

PRODUCT DATA SHEET

Sikafloor®-156

2-PART EPOXY PRIMER, LEVELLING MORTAR AND MORTAR SCREED

DESCRIPTION

Sikafloor®-156 is a two part, low viscosity epoxy resin. "Total solid epoxy composition according to the test method Deutsche Bauchemie e.V. (German Association for construction chemicals)"

USES

- Sikafloor®-156 may only be used by experienced professionals.
- For priming concrete substrates, cement screeds and epoxy mortars
 - For normal to strongly absorbent surfaces
 - Primer for all Sika Epoxy and PUR floorings
 - Binder for levelling mortars and mortar screeds
 - For internal and external use

CHARACTERISTICS / ADVANTAGES

- Low viscosity
- Good penetration ability
- High bond strength
- Easy application
- Short waiting times
- Multi-purpose
- For external use also

APPROVALS / STANDARDS

- Synthetic resin screed material according to EN 13813:2002, Declaration of Performance 02 08 01 02 007 0 00001 1008, certified by notified factory production control certification body 0921, and provided with the CE marking.
- Coating for surface protection of concrete according to EN 1504-2:2004, Declaration of Performance 02 08 01 02 007 0 00001 1008, certified by notified factory production control certification body 0921, and provided with the CE marking.

PRODUCT INFORMATION

Chemical Base	Epoxy	
Packaging	Part A	12 kg containers
	Part B	4 kg containers
	Bulk packaging	
	Part A	180 kg drums
	Part B	180 kg drums
Appearance / Colour	Resin - part A	transparent, liquid
	Hardener - part B	brownish, liquid
Shelf Life	24 months from date of production	
Storage Conditions	The product must be stored properly in original, unopened and undamaged sealed packaging, in dry conditions at temperatures between +5°C and +30 °C.	

Density	Part A	~ 1.10 kg /l	(DIN EN ISO 2811-1)
	Part B	~ 1.02 kg /l	
	Mixed resin	~ 1.1 kg /l	

All density values at 23°C.

Solid content by weight ~100 %

Solid content by volume ~100 %

TECHNICAL INFORMATION

Shore D Hardness ~83 (7 days / +23 °C / 50 % r.h.) (DIN 53505)

Compressive Strength ~55 N/mm² (Mortar, 30 days / +23 °C / 50 % r.h.) (EN 196-1)
Mortar screed: Sikafloor®-156 mixed 1:10 with suitable sand mixture, see "Systems"

Flexural Strength ~15 N/mm² (Mortar, 30 days / +23 °C / 50 % r.h.) (EN 196-1)
Mortar screed: Sikafloor®-156 mixed 1:10 with suitable sand mixture, see "Systems"

Tensile Adhesion Strength >1.5 N/mm² (failure in concrete) (EN 4624)

SYSTEM INFORMATION

Systems

Primer

Low / medium porosity concrete 1 × Sikafloor®-156

High porosity concrete 2 × Sikafloor®-156

Levelling mortar fine (surface roughness <1 mm)

Primer 1 × Sikafloor®-156

Levelling mortar 1 × Sikafloor®-156 + Sika® Aggregate-508 + Extender T

Levelling mortar medium (surface roughness up to 2 mm)

Primer 1 × Sikafloor®-156

Levelling mortar 1 × Sikafloor®-156 + Sika® Aggregate-508 + Extender T

Epoxy screed (15–20 mm layer thickness) / repair mortar

Primer 1 × Sikafloor®-156

Bonding bridge 1 × Sikafloor®-156

Screed 1 × Sikafloor®-156 + Sika® Aggregate-506

In practice the following sand mixtures proved to be suitable (grain size distribution for layer thicknesses of 15–20 mm):

25 pbw quartz sand 0.1–0.5 mm

25 pbw quartz sand 0.4–0.7 mm

25 pbw quartz sand 0.7–1.2 mm

25 pbw quartz sand 2–4 mm

Note: The largest grain size should be a maximum 1/3 of the finished layer thickness. Dependent on the grain shape and application temperatures, the aggregates and the most suitable mix should be selected.

APPLICATION INFORMATION

Mixing Ratio Part A : part B = 75 : 25 (by weight)

Consumption

Coating System	Product	Consumption
Priming	1–2 × Sikafloor®-156	1–2 × 0.30–0.50 kg/m ²
Levelling mortar fine (surface roughness < 1 mm)	1 pbw Sikafloor®-156 + 0.5 pbw Sika® Aggregate-508 + 0.015 pbw Extender T	1.4 kg/m ² /mm
Levelling mortar medium (surface roughness up to 2 mm)	1 pbw Sikafloor®-156 + 1 pbw Sika® Aggregate-508 + 0.015 pbw Extender T	1.6 kg/m ² /mm
Bonding bridge	1–2 × Sikafloor®-156	1–2 × 0.3–0.5 kg/m ²
Epoxy screed (15–20 mm layer thickness) / Repair Mortar	1 pbw Sikafloor®-156 + 6 pbw Sika® Aggregate-506	2.2 kg/m ² /mm

Note: These figures are theoretical and do not allow for any additional material required due to surface porosity, surface profile, variations in level or wastage etc.

Ambient Air Temperature	+10 °C min. / +30 °C max.								
Relative Air Humidity	80 % r.h. max.								
Dew Point	Beware of condensation! The substrate and uncured floor must be at least 3 °C above dew point to reduce the risk of condensation or blooming on the floor finish. Note: Low temperatures and high humidity conditions increase the probability of blooming.								
Substrate Temperature	+10 °C min. / +30 °C max.								
Substrate Moisture Content	< 4 % pbw moisture content using the Sika® - Tramex meter (at the time of application). Test method: Sika®-Tramex meter, CM - measurement or oven-dry-method. No rising moisture according to ASTM (Polyethylene-sheet).								
Pot Life	<table><thead><tr><th>Temperature</th><th>Time</th></tr></thead><tbody><tr><td>+10 °C</td><td>~ 60 minutes</td></tr><tr><td>+20 °C</td><td>~ 30 minutes</td></tr><tr><td>+30 °C</td><td>~ 15 minutes</td></tr></tbody></table>	Temperature	Time	+10 °C	~ 60 minutes	+20 °C	~ 30 minutes	+30 °C	~ 15 minutes
Temperature	Time								
+10 °C	~ 60 minutes								
+20 °C	~ 30 minutes								
+30 °C	~ 15 minutes								

Curing Time

Before applying solvent free products on Sikafloor®-156 allow:

Substrate temperature	Minimum	Maximum
+10 °C	24 hours	4 days
+20 °C	12 hours	2 days
+30 °C	8 hours	24 hours

Before applying solvent containing products on Sikafloor®-156 allow:

Substrate temperature	Minimum	Maximum
+10 °C	36 hours	6 days
+20 °C	24 hours	4 days
+30 °C	12 hours	2 days

Times are approximate and will be affected by changing ambient conditions particularly temperature and relative humidity.

APPLICATION INSTRUCTIONS

SUBSTRATE QUALITY / PRE-TREATMENT

- The concrete substrate must be sound and of sufficient compressive strength (minimum 25 N/mm²) with a minimum pull off strength of 1.5 N/mm².
- The substrate must be clean, dry and free of all contaminants such as dirt, oil, grease, coatings and surface treatments, etc.
- Concrete substrates must be prepared mechanically using abrasive blast cleaning or scarifying equipment

to remove cement laitance and achieve an open textured surface.

- Weak concrete must be removed and surface defects such as blow holes and voids must be fully exposed.
- Repairs to the substrate, filling of blowholes/voids and surface levelling must be carried out using appropriate products from the Sikafloor®, Sikadur® and Sikagard® range of materials.
- All dust, loose and friable material must be completely removed from all surfaces before application of the product, preferably by brush or vacuum.

MIXING

Prior to mixing, stir part A mechanically. When all of part B has been added to part A, mix continuously for 3 minutes until a uniform mix has been achieved. When parts A and B have been mixed, add the quartz sand and if required the Extender T and mix for a further 2 minutes until a uniform mix has been achieved. To ensure thorough mixing pour materials into another container and mix again to achieve a consistent mix. Over mixing must be avoided to minimise air entrainment.

Mixing Tools

Sikafloor®-156 must be thoroughly mixed using a low speed electric stirrer (300 - 400 rpm) or other suitable equipment. For the preparation of mortars use a forced action mixer of rotating pan, paddle or trough type. Free fall mixers should not be used.

APPLICATION

Prior to application, confirm substrate moisture content, relative air humidity and dew point. If > 4% pbw moisture content, Sikafloor® EpoCem® may be applied as a T.M.B. (temporary moisture barrier) system.

Primer:

Make sure a continuous, pore free coat covers the substrate. If necessary, apply two priming coats. Apply Sikafloor®-156 by brush, roller or squeegee. Preferred application is by using a squeegee and then back-rolling crosswise.

Levelling mortar:

Rough surfaces need to be levelled first. Apply the levelling mortar by squeegee/trowel to the required thickness.

Bonding bridge:

Apply Sikafloor®-156 by brush, roller or squeegee. Preferred application is by using a squeegee and then backrolling crosswise.

Epoxy screed / repair mortar:

Apply the mortar screed evenly on the still "tacky" bonding bridge, using levelling battens and screed rails as necessary. After a short waiting time compact and smoothen the mortar with a trowel or Teflon coated power float (usually 20 - 90 rpm).

CLEANING OF TOOLS

Clean all tools and application equipment with Thinner C immediately after use. Hardened and/or cured material can only be removed mechanically.

FURTHER DOCUMENTS

Substrate quality & Preparation

Please refer to Sika Method Statement: "EVALUATION AND PREPARATION OF SURFACES FOR FLOORING SYSTEMS".

Application instructions

Please refer to Sika Method Statement: "MIXING & APPLICATION OF FLOORING SYSTEMS".

Maintenance

Please refer to "Sikafloor®- CLEANING REGIME".

LIMITATIONS

- Do not apply Sikafloor®-156 on substrates with rising moisture.
- Freshly applied Sikafloor®-156 should be protected from damp, condensation and water for at least 24 hours.
- Sikafloor®-156 mortar screed is not suitable for frequent or permanent contact with water unless sealed.
- Practical trials should be carried out for mortar mixes to assess suitable aggregate grain size distribution.
- For external applications, apply on a falling temperature. If applied during rising temperatures "pin holing" may occur from rising air.
- These pinholes can be closed after a soft grinding by applying a scratch coat of Sikafloor®-156 mixed with approx. 3 % of Extender T.
- Under certain conditions, underfloor heating or high ambient temperatures combined with high point loading, may lead to imprints in the resin. If heating is required do not use gas, oil, paraffin or other fossil fuel heaters, these produce large quantities of both CO₂ and H₂O water vapour, which may adversely affect the finish. For heating use only electric powered warm air blower systems.
- The incorrect assessment and treatment of cracks may lead to a reduced service life and reflective cracking.

Construction joints require pre-treatment. Treat as follows:

- Static Cracks: prefill and level with Sikadur® or Sikafloor® epoxy resin
- Dynamic cracks: to be assessed and if necessary apply a stripe coat of elastomeric material or design as a movement joint

Tools:

Recommended supplier of tools:
PPW-Polyplan-Werkzeuge GmbH, Phone: +49 40/5597260, www.polyplan.com

BASIS OF PRODUCT DATA

All technical data stated in this Product Data Sheet are based on laboratory tests. Actual measured data may vary due to circumstances beyond our control.

LOCAL RESTRICTIONS

Please note that as a result of specific local regulations the performance of this product may vary from country to country. Please consult the local Product Data Sheet for the exact description of the application fields.

ECOLOGY HEALTH AND SAFETY

For information and advice on the safe handling, storage and disposal of chemical products, users shall refer to the most recent Safety Data Sheet (SDS) containing physical, ecological, toxicological and other safety-related data.

DIRECTIVE 2004/42/CE - LIMITATION OF EMISSIONS OF VOC

According to the EU-Directive 2004/42, the maximum allowed content of VOC (Product category IIA / j type sb) 500 g/l (Limit 2010) for the ready to use product. The maximum content of Sikafloor®-156 is < 500 g/l VOC for the ready to use product.

LEGAL NOTES

The information, and, in particular, the recommendations relating to the application and end-use of Sika products, are given in good faith based on Sika's current knowledge and experience of the products when properly stored, handled and applied under normal conditions in accordance with Sika's recommendations. In practice, the differences in materials, substrates and actual site conditions are such that no warranty in respect of merchantability or of fitness for a particular purpose, nor any liability arising out of any legal relationship whatsoever, can be inferred either from this information, or from any written recommendations, or from any other advice offered. The user of the product must test the product's suitability for the intended application and purpose. Sika reserves the right to change the properties of its products. The proprietary rights of third parties must be observed. All orders are accepted subject to our current terms of sale and delivery. Users must always refer to the most recent issue of the local Product Data Sheet for the product concerned, copies of which will be supplied on request. It may be necessary to adapt the above disclaimer to specific local laws and regulations. Any changes to this disclaimer may only be implemented with permission of Sika® Corporate Legal in Baar.

Sika (NZ) Limited
85-91 Patiki Road
Avondale, Auckland 1026
New Zealand
0800 745 269
www.sika.co.nz



Product Data Sheet
Sikafloor®-156
August 2018, Version 05.01
020811020010000007

Sikafloor-156-en-NZ-(08-2018)-5-1.pdf

