

BUILDING TRUST

SYSTEM DATA SHEET Sikafloor[®] PurCem[®] HS-21

Heavy duty, smooth finish polyurethane cement hybrid flooring system



DESCRIPTION

Sikafloor[®] PurCem[®] HS-21 is a self-smoothing coloured flooring screed suitable for areas subject to medium temperature shocks and heavy loading, abrasion and chemical exposure. Sikafloor[®] PurCem[®] HS-21 is based on polyurethane cement technology and is part of the Sikafloor[®] PurCem[®] flooring range.

USES

Sikafloor[®] PurCem[®] HS-21 may only be used by experienced professionals.

The System can be used in industrial buildings such as:

- Chemical and processing facilities
- Food and beverage facilities
- Catering and industrial kitchens
- Manufacturing facilities and workshops
- Mining and metal processing facilities
- Recycling plants

SYSTEM INFORMATION

CHARACTERISTICS / ADVANTAGES

- High abrasion resistance
- Good resistance to specific chemicals
- Easy to clean and maintain
- Good impact resistance
- Low maintenance
- Seamless and hygienic
- Tolerant to substrates with high moisture content

APPROVALS / STANDARDS

 Slip resistance DIN EN 16165, MPI, Test certificate No. 12 10552 - S/ 22

System Structure	Layer	Product		
	1. Primer or scratch coat	Sikafloor [®] -21 PurCem [®]		
		Optional primers before scratch coat:		
		Sikafloor [®] -150		
		Sikafloor [®] -151		
		Sikafloor [®] -501 Agrregate broadcast		
		in excess.		
		Refer to the individual Product Data		
		Sheets.		
	2. Wearing layer	Sikafloor [®] -21 PurCem [®]		
Composition	Water-based polyurethane cem	Water-based polyurethane cement hybrid		
Appearance	Cured system appearance	Smooth matt finish		

SYSTEM DATA SHEET Sikafloor® PurCem® HS-21 December 2023, Version 05.01 02081490000000008 Cured system colour

Contact your Sika representative for available colours

Nominal thickness

4 mm to 6 mm

TECHNICAL INFORMATION

Compressive Strength	Cured 28 days at +23	°C > 55 MPa	(EN 13892-2)	
Tensile Adhesion Strength	≥ 2.0 (1.5) MPa		(EN 1542)	
Reaction to Fire	Class B _{fl} -s1	Class B _{fl} -s1 (EN 13501-1)		
Chemical Resistance	Refer to the chemica	Refer to the chemical resistance of Sikafloor [®] -21 PurCem [®]		
Skid / Slip Resistance	Class	R 9	(DIN 51130)	
Service Temperature	System thickness	Minimum	Maximum	
	4 mm	-5 °C	+80 °C	
	6 mm	-5 °C	+90 °C	

APPLICATION INFORMATION

Consumption	Layer	Layer Product			
	Primer or scratch coat	Sikafloor®-21 PurCem®	~1.0-3.0 kg/m ²		
	Wearing layer	Sikafloor [®] -21 PurCem [®]	~1.9 kg/m²per mm thickness		
Ambient Air Temperature	Minimum +10 °C				
	Maximum	+35 °C			
Relative Air Humidity	Maximum 80 %				
Dew Point	Beware of condensation! The substrate and uncured floor must be at least 3 °C above dew point to reduce the risk of condensation or other disturbance of the surface on the floor finish.				
Substrate Temperature	Minimum	Minimum +10 °C			
	Maximum +35 °C				
Substrate Moisture Content	No rising moisture according to ASTM (Polyethylene-sheet). Osmosis caused by rising moisture is not covered by the product warranty Can be installed on substrates with higher moisture content. No ponding water. The substrate needs to be visibly dry and have adequate pull-off strength min 1.5 MPa Note: Epoxy primers are not suitable for application onto a high substrate moisture content.				
	Can be installed on sub ponding water. The sub pull-off strength min 1. Note: Epoxy primers ar	strates with higher moistu ostrate needs to be visibly 5 MPa	re content. No dry and have adequate		
	Can be installed on sub ponding water. The sub pull-off strength min 1. Note: Epoxy primers ar moisture content.	strates with higher moistu ostrate needs to be visibly 5 MPa	ire content. No dry and have adequate on onto a high substrate		
	Can be installed on sub ponding water. The sub pull-off strength min 1. Note: Epoxy primers ar moisture content. <u>Temperature</u> Foo	strates with higher moistu ostrate needs to be visibly 5 MPa e not suitable for applicati	ire content. No dry and have adequate on onto a high substrate		
Applied Product Ready for Use	Can be installed on sub ponding water. The sub pull-off strength min 1. Note: Epoxy primers ar moisture content. Temperature Foo +10 °C ~20	strates with higher moistupstrate needs to be visibly 5 MPa e not suitable for applicati t traffic Light traffic	ore content. No dry and have adequate on onto a high substrate Full cure		

SYSTEM DATA SHEET Sikafloor® PurCem® HS-21 December 2023, Version 05.01 02081490000000008



BUILDING TRUST

BASIS OF PRODUCT DATA

All technical data stated in this Product Data Sheet are based on laboratory tests. Actual measured data may vary due to circumstances beyond our control.

FURTHER DOCUMENTS

- Sikafloor[®] PurCem[®] Method Statement
- Sika[®] Method Statement Mixing and Application of Flooring Systems
- Sika[®] Method Statement Surface Evaluation & Preparation
- Sikafloor[®] PurCem[®] Product Data Sheets

ECOLOGY HEALTH AND SAFETY

For information and advice on the safe handling, storage and disposal of chemical products, users shall refer to the most recent Safety Data Sheet (SDS) containing physical, ecological, toxicological and other safety-related data.

LOCAL RESTRICTIONS

Please note that as a result of specific local regulations the performance of this product may vary from country to country. Please consult the local Product Data Sheet for the exact description of the application fields.

LEGAL NOTES

The information, and, in particular, the recommendations relating to the application and end-use of Sika products, are given in good faith based on Sika's current knowledge and experience of the products when properly stored, handled and applied under normal conditions in accordance with Sika's recommendations. In practice, the differences in materials, substrates and actual site conditions are such that no warranty in respect of merchantability or of fitness for a particular purpose, nor any liability arising out of any legal relationship whatsoever, can be inferred either from this information, or from any written recommendations, or from any other advice offered. The user of the product must test the product's suitability for the intended application and purpose. Sika reserves the right to change the properties of its products. The proprietary rights of third parties must be observed. All orders are accepted subject to our current terms of sale and delivery. Users must always refer to the most recent issue of the local Product Data Sheet for the product concerned, copies of which will be supplied on request. It may be necessary to adapt the above disclaimer to specific local laws and regulations. Any changes to this disclaimer may only be implemented with permission of Sika® Corporate Legal in Baar.

Sika (NZ) Limited 85-91 Patiki Road Avondale, Auckland 1026 New Zealand 0800 745 269 www.sika.co.nz



SYSTEM DATA SHEET Sikafloor® PurCem® HS-21 December 2023, Version 05.01 02081490000000008 SikafloorPurCemHS-21-en-NZ-(12-2023)-5-1.pdf



BUILDING TRUST