

BUILDING PRODUCT INFORMATION SHEET

Pulastic® Multicoat E

2-part polyurethane matt coloured finish coating

DESCRIPTION

Pulastic Multicoat E is a coloured two part water-based, very low VOC, polyurethane matt finish coat for Pulastic sports flooring systems.

USES

Pulastic Multicoat E is a durable, high quality coloured coating that meets the most stringent V.O.C. regulations in Europe and the USA known today. The product is mainly used for the installation of seamless sports flooring systems. We recommend that the manufacturer is consulted regarding alternative applications other than the standard sports flooring systems.

This water based coating offers the optimum friction properties for sports, has a long-term very mat appearance, a high abrasion resistance, a high colour fastness and a high resistance against the usual cleaning agents. Moreover the coating has good bonding properties and is permanently flexible. The balanced viscosity liquid consistency assures a uniform texture all over the area when roller applied.

The nature of the product requires (manufacturer) trained specialists to execute the application.

FEATURES

Waterbased Very low odour Good UV resistance, non-yellowing-
Silky-gloss Easy to clean

PRODUCT INFORMATION

Product identifier	Pulastic® Multicoat E
Place of manufacture	Overseas
Packaging	Part A: 8.5 kg Part B: 1.5 kg Part C: 1.0 kg Part A+B: 11 kg ready to mix units
Shelf life	12 months from date of production of the B part, if stored properly in original, unopened and undamaged sealed packaging.
Storage conditions	in dry conditions at temperatures between +5°C and +30°C.
Colour	16 as per standard colour card
Appearance and colour	Pulastic Multicoat E is silky-gloss after final curing. Available in various colour shades and as substrates for local tinting.
Density	Part A: ~ 1.05 kg/l Part B: ~ 1.13 kg/l Part C: ~ 1.00 kg/l Mixed Resin: ~ 1.06 kg/l All Density values at +23°C.

TECHNICAL INFORMATION

Gloss level	3%
Solar reflectance	8 (excellent)
Chemical resistance	Resistant to many chemicals. Please ask for a detailed chemical resistance table.

APPLICATION INFORMATION

Consumption	ca. 0.13 kg/m ² per layer
--------------------	--------------------------------------

This figure is theoretical and do not allow for any additional material due to surface porosity, surface profile, variations in level and wastage etc. Lower consumption can cause roller marks, gloss differences and irregular surface structure, higher consumption result in water retention.

Ambient air temperature	+10°C min. / +30°C max.			
Relative air humidity	75% max. During curing the humidity should not exceed 75 % max. Adequate fresh air ventilation must be provided to remove the excess moisture from the curing product.			
Dew point	Beware of condensation! The substrate and uncured floor must be at least 4°C above the dew point to reduce the risk of condensation or blooming on the floor finish.			
Substrate temperature	+10°C min. / +30°C max.			
Pot Life	Temperature	Time		
	+10°C	~ 50 minutes		
	+20°C	~ 30 minutes		
	+30°C	~ 20 minutes		
Curing time	Temperature	Foot Traffic	Light Traffic	Full Cure
	+10°C	~ 30 hours	~ 48 hours	~ 6 hours
	+20°C	~ 16 hours	~ 24 hours	~ 4 hours
	+30°C	~ 12 hours	~ 18 hours	~ 3 hours

MANUFACTURER AND IMPORTER INFORMATION

Manufacturer information	Address	Sika Supply Centre AG Industriestrasse 26 6060, Sarnen Switzerland		
Importer information	Address	Sika (NZ) Limited 85-91 Patiki Road Avondale, Auckland 1026 New Zealand		
	Phone number	0800 745 269		
	Website	https://nzl.sika.com/		
	Email address	info@nz.sika.com		
	NZBN	9429000018791		

BUILDING CODE INFORMATION

Building Code clauses	B2 Durability: Performance clause B2.3.1 - (c) 5 years
	C3 Fire Affecting Areas Beyond the Fire Source. Performance clause C3.4(b)
	F2 Hazardous Building Materials: Performance clause F2.3.1
Building Code compliance statements	Performance B2.3.1 - (c) 5 years. This product has been assessed in accordance with B2/VM1. It achieves this durability requirement and will remain serviceable for 5 years, or more, when installed and maintained in accordance with the relevant Sika technical literature. nzl.sika.com . According to Sika's "Service Improvement" records, maintained within its ISO9001:2015 Quality Management System, this product has performed successfully since it was introduced in 2012.
	Performance C3.4(b) The installed system has been fire tested in accordance with ISO 9239-1 : 2010. It has a critical radiant flux that exceeds 4.5 kW/m ² and can be used in all areas of the building, as defined in this clause.

Performance F2.3.1: This product meets this requirement when used and applied in accordance with Sika's installation instructions and does not present a health hazard to people occupying or using the building. Refer to the Sika Product Technical Data sheet and product Safety Data Sheet nzl.sika.com for further information if required

BASIS OF PRODUCT DATA

All technical data in this document are based on laboratory tests. Actual measured data may vary due to circumstances beyond our control.

IMPORTANT CONSIDERATIONS

Freshly applied Pulastic Multicoat E must be protected from damp, condensation and water for at least 7 days (+20°C). Unevenness of substrates as well as inclusions of dirt cannot be covered by thin sealers coats. Therefore substrate and adjacent areas must be cleaned thoroughly prior to application. Tools Electric drill, mixing-blade, brushes and short pill rollers 10 up to 70 cm for surface area – amount depending on size of floor). Roller frames and telescopic extension handles, tape and spatula. Plastic sheeting for placement of wet rollers. If heating is required do not use gas, oil, paraffin or other fossil fuel heaters, these produce large quantities of both CO₂ and H₂O water vapour, which may adversely affect the finish. For heating use only electric powered warm air blower systems.

ECOLOGY, HEALTH AND SAFETY

For information and advice on the safe handling, storage and disposal of chemical products, users shall refer to the most recent Safety Data Sheet (SDS) containing physical, ecological, toxicological and other safety-related data.

APPLICATION INSTRUCTIONS

DESIGN REQUIREMENTS

This product is part of a system that includes primers and other associated products. For full design information refer to the relevant Sika literature available at nzl.sika.com. For further information or support phone 0800SIKANZ

INSTALLATION REQUIREMENTS

This system of products may only be installed by a Sika trained and approved applicator. For further information contact 0800SIKANZ

SUBSTRATE QUALITY

The substrate must be clean, dry and free of all contaminants such as dirt, oil, grease, coatings and surface treatments, etc. Pull-off strength must be not less than 1.5 MPa. If in doubt, apply a test area first.

SUBSTRATE PREPARATION

All dust, loose and friable material must be completely removed from all surfaces before application of the product, preferably by brush or vacuum.

MIXING

Part A : part B : Part C = 77 : 14 : 9 (by weight)

Prior to mixing, stir part A mechanically. When all of part B has been added to part A, mix continuously for 3 minutes until a uniform mix has been achieved. After mixing A+B, add C. After adding, continuously for 1 minute. Wait 1 minute and then mix it up again for 1 minute. Adding of part C must be the same in every mix, if not it could slightly influence the texture of the final result. Check the mixing result and the absence of lumps or agglomerates on a mixing blade. To ensure thorough mixing pour materials into another container and mix again to achieve a consistent mix. Over mixing must be avoided to minimise air entrainment.

Mixing Tools Pulastic Multicoat E must be thoroughly mixed using an electric mixer or equivalent.

APPLICATION

Prior to application confirm relative air humidity and dew point! During installation and curing of the Pulastic Multicoat E it is of major importance to determine exactly the degree of humidity of the working area. Too humid conditions during installation and curing may result in colour deviation, inconsistent appearance of the floor ("cloudy effect") and reduced strength of the coating layer. The appearances mentioned above can be avoided if the dew point of the room is determined exactly, before starting the coating application. The dew point determines at what temperature, condensation will take place on the floor surface. Condensation of humidity must be avoided at all times for two reasons: 1) At a too high humidity in the room the water in the coating will have great difficulties evaporating, or will not evaporate at all. The speed of evaporation of water in the PULASTIC Multicoat E is directly related to difference between the dew point and the floor-temperature. The closer the floor-temperature is to the dew point, the slower the coating will dry. Even if the floor-temperature is equal to the dew point, the coating will stop drying completely. 2) Curing of a 2-component, waterborne PU system exists of 2 processes. First the evaporating of the water. Secondly curing of the A- with the B-component. Important to note that the B-component also reacts with water. If evaporation takes too long, a relatively too big part of the B-component will react with the water of the coating and reaction between A and B component may be insufficient, resulting in the deviations mentioned above such as cloudy effects in the floor and/or lower coating abrasion resistance. Basically the following working conditions must be respected*: Temperature of material and working area: 10°C-30°C. Temperature of sub floor: minimal 4°C above the Dew-point. Air humidity: max 75%. If ventilation possibilities are only very limited, the conditions are even more critical and must be respected as follows*: Temperature of material and working area: 10°- 30°C. Temperature of sub floor: minimal 5°C above the Dew-point. Air humidity: max 70%. *During Application and Curing!

CLEANING OF EQUIPMENT

Clean all tools and application equipment with water immediately after use. Hardened and/or cured material can only be removed mechanically.

MAINTENANCE INSTRUCTIONS

To maintain the appearance of the floor after application, Pulastic Multicoat E must have all spillages removed immediately and be regularly cleaned. Please refer to the "General maintenance tips and recommended cleaning procedures" for the PULASTIC Solid Floor Systems.

LOCAL RESTRICTIONS

Note that as a result of specific local regulations the declared data and recommended uses for this product may vary from country to country. Consult the local Product Data Sheet for the exact product data and uses.

LEGAL NOTES

The information, and, in particular, the recommendations relating to the application and end-use of Sika products, are given in good faith based on Sika's current knowledge and experience of the

products when properly stored, handled and applied under normal conditions in accordance with Sika's recommendations. In practice, the differences in materials, substrates and actual site conditions are such that no warranty in respect of merchantability or of fitness for a particular purpose, nor any liability arising out of any legal relationship whatsoever, can be inferred either from this information, or from any written recommendations, or from any other advice offered. The user of the product must test the product's suitability for the intended application and purpose. Sika reserves the right to change the properties of its products. The proprietary rights of third parties must be observed. All orders are accepted subject to our current terms of sale and delivery. Users must always refer to the most recent issue of the local Product Data Sheet for the product concerned, copies of which will be supplied on request. It may be necessary to adapt the above disclaimer to specific local laws and regulations. Any changes to this disclaimer may only be implemented with permission of Sika® Corporate Legal in Baar.

The building product/building product line is not subject to warning or ban under section 26 of the Building Act 2004.

Sika (NZ) Limited

85-91 Patiki Road
Avondale, Auckland 1026
New Zealand
0800 745 269
www.sika.co.nz

NZ BUILDING PRODUCT INFORMATION SHEET

Pulastic® Multicoat E
12/12/2024 File version 1.0
020812060020000009

NZBPIS-6887-7502-7502-en-GB-1.0