

PRODUCT DATA SHEET

Pulastic® Multicoat E Clear

Transparent 2-part PU silky-gloss coat for use in systems of the PULASTIC Sports Floor range.

SIKA NZ
APPROVED
CONTRACTOR
ONLY

DESCRIPTION

Pulastic Multicoat Clear (E) is a transparent two part water-based, very low VOC, polyurethane, silky-gloss seal coat.

USES

Pulastic® Multicoat E Clear may only be used by experienced professionals.

Transparent, silky-gloss seal coat for PULASTIC Solid Line Systems

CHARACTERISTICS / ADVANTAGES

- Waterbased
- Very low odour
- Good UV resistance, non-yellowing
- Easy to clean

APPROVALS / STANDARDS

Fire classification acc. to EN 13501-1 Report No. 2008-B-3883/10, MPA Dresden

PRODUCT INFORMATION

Chemical Base	POLYURETHANE
Packaging	Part A: 6.0 kg Part B: 1.5 kg Part A+B: 7.5 kg ready to mix units
Colour	Pulastic Multicoat Clear E is silky-gloss after final curing.
Shelf Life	6 months both for A and C component, from date of production if stored properly in original, unopened and undamaged sealed packaging
Storage Conditions	in dry conditions at temperatures between +5°C and +30°C.

APPLICATION INFORMATION

Mixing Ratio	Part A : part B = 80: 20 (by weight)
Consumption	0.13 kg/m ² /layer
Ambient Air Temperature	+10°C min. / +30°C max.
Relative Air Humidity	75% max. During curing the humidity should not exceed 75 % max. Adequate fresh air ventilation must be provided to remove the excess moisture from the curing product.

Dew Point	Beware of condensation! The substrate and uncured floor must be at least 3°C above the dew point to reduce the risk of condensation or blooming on the floor finish.			
Substrate Temperature	+10°C min. / +30°C max.			
Pot Life	Temperature	Time		
	+10	+/- 50 min		
	+20	+/- 30 min		
	+30	+/- 20 min		
Curing Time	Temperature	Foot traffic	Light traffic	Full cure
	+10°C	~ 30 hours	~ 48 hours	~ 6 days
	+20°C	~ 16 hours	~ 24 hours	~ 4 days
	+30°C	~ 12 hours	~ 18 hours	~ 3 days

SYSTEM INFORMATION

System Structure	Sealing of systems of Pulastic Solid Line range: Base coat: 1 x PULASTIC Coating 222W Silky-gloss seal coat: 1 x Pulastic Multicoat Clear (E)
-------------------------	---

BASIS OF PRODUCT DATA

All technical data stated in this Product Data Sheet are based on laboratory tests. Actual measured data may vary due to circumstances beyond our control.

FURTHER DOCUMENTS

Freshly applied PULASTIC Multicoat Clear (E) must be protected from damp, condensation and water for at least 7 days (+20°C). Unevenness of substrates as well as inclusions of dirt / marks cannot be covered by thin sealers coats. Therefore substrate and adjacent areas must be cleaned thoroughly prior to application.

Tools

Electric drill, mixing-blade, brushes and short piller rollers

If heating is required do not use gas, oil, paraffin or other fossil fuel heaters, these produce large quantities of both CO₂ and H₂O water vapour, which may adversely affect the finish. For heating use only electric powered warm air blower systems.

ECOLOGY HEALTH AND SAFETY

APPLICATION INSTRUCTIONS

SUBSTRATE QUALITY

The substrate must be clean, dry and free of all contaminants such as dirt, oil, grease, coatings and surface treatments, etc. Pull-off strength must be not less than 1.5 MPa. If in doubt, apply a test area first.

SUBSTRATE PREPARATION

All dust, loose and friable material must be completely removed from all surfaces before application of the product, preferably by brush or vacuum.

MIXING

Prior to mixing, stir part A mechanically. When all of part B has been added to part A, mix continuously for 3 minutes until a uniform mix has been achieved. To achieve smoother surface 5 % water can be added. After adding the water mix continuously for 1 minute. Wait one minute and then mix it up again for one minute.

The adding of water must be the same in every mix, if not it could slightly influence the paleness and the texture.

Check the mixing result and the absence of lumps or agglomerates on a mixing blade.

To ensure thorough mixing pour materials into another container and mix again to achieve a consistent mix. Over mixing must be avoided to minimise air entrainment.

Multicoat Clear (E) must be thoroughly mixed using an electric mixer or equivalent.

APPLICATION

Prior to application confirm relative air humidity and dew point!

During installation and curing of the PULASTIC Multicoat Clear (E) it is of major importance to determine exactly the degree of humidity of the working area. Too humid conditions during installation and curing may result in colour deviation, inconsistent appearance of the floor ("cloudy effect") and reduced strength of the coating layer.

The appearances mentioned above can be avoided if the dew point of the room is determined exactly, before starting the coating application. The dew point determines at what temperature, condensation will take place on the floor surface. Condensation of humidity must be avoided at all times for two reasons:

- 1) At a too high humidity in the room the water in the coating will have great difficulties evaporating, or will not evaporate at all. The speed of evaporation of water in the PULASTIC Multicoat Clear (E) is directly related to difference between the dew point and the floor-temperature. The closer the floor-temperature is to the dew point, the slower the coating will dry. Even if the floor-temperature is equal to the dew point, the coating will stop drying completely.

- 2) Curing of a 2-component, waterborne PU system consists of 2 processes. First the evaporating of the water. Secondly curing of the A- with the B-component. Important to note that the B-component also reacts with water. If evaporation takes too long, too much of the B-component will react with the water of the coating and reaction between A and B component may be insufficient, resulting in the deviations mentioned above such as cloudy effects in the floor and/or lower coating abrasion resistance.

Basically the following working conditions must be respected*:

Temperature of material and working area: 10°C-30°C.
Temperature of sub floor: minimal 4°C above the Dew-point.

Air humidity: max 75%.

If ventilation possibilities are only very limited, the conditions are even more critical and must be respected as follows*:

Temperature of material and working area: 10°- 30°C.
Temperature of sub floor: minimal 5°C above the Dew-point.

Air humidity: max 70%.

CLEANING OF TOOLS

Clean all tools and application equipment with water immediately after use. Hardened and/or cured material can only be removed mechanically.

Sika (NZ) Limited

85-91 Patiki Road
Avondale, Auckland 1026
New Zealand
0800 745 269
www.sika.co.nz



Product Data Sheet

Pulastic® Multicoat E Clear
January 2025, Version 01.01
020812060020000014

LOCAL RESTRICTIONS

Please note that as a result of specific local regulations the performance of this product may vary from country to country. Please consult the local Product Data Sheet for the exact description of the application fields.

LEGAL NOTES

The information, and, in particular, the recommendations relating to the application and end-use of Sika products, are given in good faith based on Sika's current knowledge and experience of the products when properly stored, handled and applied under normal conditions in accordance with Sika's recommendations. In practice, the differences in materials, substrates and actual site conditions are such that no warranty in respect of merchantability or of fitness for a particular purpose, nor any liability arising out of any legal relationship whatsoever, can be inferred either from this information, or from any written recommendations, or from any other advice offered. The user of the product must test the product's suitability for the intended application and purpose. Sika reserves the right to change the properties of its products. The proprietary rights of third parties must be observed. All orders are accepted subject to our current terms of sale and delivery. Users must always refer to the most recent issue of the local Product Data Sheet for the product concerned, copies of which will be supplied on request. It may be necessary to adapt the above disclaimer to specific local laws and regulations. Any changes to this disclaimer may only be implemented with permission of Sika® Corporate Legal in Baar.

PulasticMulticoatEClear-en-NZ-(01-2025)-1-1.pdf