

PRODUCT DATA SHEET

SikaGrout®-212 HP NZ

Shrinkage compensated high strength cementitious grout

DESCRIPTION

SikaGrout®-212 HP NZ is a cementitious grout containing a carefully formulated blend of aggregates and other materials, plus Sika admixtures, that enables it to achieve high early age and long term strengths. SikaGrout®-212 HP NZ has been designed to incorporate a two stage process that counteracts the effects of shrinkage often associated with cement grouts. Sika Grouts contain materials that provide positive expansion in the plastic phase and shrinkage compensation once hardened. Sika Grouts are normally used in details where the material can be confined and restrained during placement and curing to optimise these characteristics. SikaGrout®-212 HP NZ is a one component grout and only requires mixing with clean, fresh water.

USES

SikaGrout®-212 HP NZ is ideal for many types of structural grouting applications where high early age and/or long term compressive strengths are required. It can be mixed to different stages of fluidity to produce the desired level of workability. Add the required amount of water for:-

- Trowel applied medium flow mortar
- Pourable high flow grout

Typical applications for SikaGrout®-212 HP NZ are:-

- Under machine foundations and base plates
- Reinforcement ducts in the connection detail between precast columns and beams
- For gaps of 6 mm to 80 mm

CHARACTERISTICS / ADVANTAGES

- High early age strength development
- Increased resistance to aggressive liquid penetration when hardened
- Very high final strengths
- Adjustable consistency
- High flow characteristics
- Positive shrinkage compensation

PRODUCT INFORMATION

Packaging	25 kg bags
Appearance / Colour	Grey powder
Shelf Life	Six (6) months from date of manufacture when stored as stated.
Storage Conditions	Store in unopened, original containers, free from frost and below +25°C.
Density	~ 2.3 kg/litre

TECHNICAL INFORMATION

Compressive Strength	24 hours	> 40 MPa	(EN 196-1)
	7 days	~ 65 MPa	
	28 days	~ 85 MPa	

APPLICATION INFORMATION

Mixing Ratio	Maximum water content: 3.5 litres / 25 kg bag
Yield	As a pourable grout: 25 kg = Approx. 12.4 litres when mixed with 3.5 litres of water

BASIS OF PRODUCT DATA

All technical data stated in this Product Data Sheet are based on laboratory tests. Actual measured data may vary due to circumstances beyond our control.

LIMITATIONS

Large volumes of cement rich grout can generate excessive amounts of heat whilst hardening as a result of the cement hydration process. This heat build up may in some cases lead to thermal cracking within the grout as it cools down. For applications requiring larger volumes it is recommended that our high strength, flowing micro concrete, Sika MonoTop®-438 R (refer separate data sheet) be used.

ECOLOGY HEALTH AND SAFETY

For information and advice on the safe handling, storage and disposal of chemical products, users shall refer to the most recent Safety Data Sheet (SDS) containing physical, ecological, toxicological and other safety-related data.

APPLICATION INSTRUCTIONS

SUBSTRATE QUALITY / PRE-TREATMENT

Surface Preparation:

- Concrete surfaces should be clean, sound and free from dust, oils, grease, loosely adhering particles or any other surface contaminants that will affect bond.
- The surface must be scabbled or sandblasted to remove all weak cement laitance.
- Dry concrete substrates shall be saturated with water for some time, and the surface allowed to dry (to achieve what is referred to as a 'saturated surface dry' condition) before grouting commences.
- Metal surfaces (iron and steel) should be free from rust, scale, oil and grease, etc

Preparation of Detail

- Formwork must be constructed to prevent any leakage of the plastic grout.
- Formwork should be constructed in such a manner as to ensure that a minimum of horizontal surface area is left exposed. The formwork must be able to rigidly confine the grout during its expansion process.
- When grouting under base plates, etc, formwork should be constructed to ensure that a head of grout higher than the level of the base plate is maintained. This will provide a constant full flow of grout under the base plate to avoid the occurrence of air entrapment under the plate.
- When filling any detail ensure that an adequate

volume of mixed grout is available to allow for a continuous and uninterrupted flow.

- In areas of formwork where air pockets may occur it is necessary to install bleed tubes or openings that will allow entrapped air to escape.
- In many cases it may be necessary to install grouting tubes or pipes that enable the cavity to be filled from bottom to top. This will force any air upwards and help to eliminate the possibility of air locks being formed.
- Ensure that any formwork has been thoroughly treated with a suitable mould release agent.

MIXING

Application temp: +5°C to +25°C. Pour the required amount of clean, fresh water into a suitable mixing container and slowly add all of the powder while mixing continuously with a Sika mixing paddle attached to a low speed electric drill (max. 500 rpm). Mix for 2-3 minutes until a smooth, lump free consistency is achieved.

APPLICATION

Flush out detail with clean, fresh water prior to grout placement. Grout should be placed into forms immediately after mixing, taking care to ensure no air is trapped.

CURING TREATMENT

Formwork should be left in place for at least 5 days if possible, to prevent moisture evaporation and provide restraint to early age hardened expansion. Once formwork is removed a suitable curing membrane such as Sika Antisol® should be applied to any exposed faces. Refer to separate data sheet for further information.

CLEANING OF TOOLS

Clean all tools and equipment with water immediately after use. Hardened SikaGrout®-212 HP NZ can only be removed mechanically.

LOCAL RESTRICTIONS

Please note that as a result of specific local regulations the performance of this product may vary from country to country. Please consult the local Product Data Sheet for the exact description of the application fields.

LEGAL NOTES

The information, and, in particular, the recommendations relating to the application and end-use of Sika products, are given in good faith based on Sika's current knowledge and experience of the products when properly stored, handled and applied under normal conditions in accordance with Sika's recommendations. In practice, the differences in materials, substrates and actual site conditions are such that no warranty in respect of merchantability or of fitness for a particular purpose, nor any liability arising out of any legal relationship whatsoever, can be inferred either from this information, or from any written recommendations, or from any other advice offered. The user of the product must test the product's suitability for the intended application and purpose. Sika re-

serves the right to change the properties of its products. The proprietary rights of third parties must be observed. All orders are accepted subject to our current terms of sale and delivery. Users must always refer to the most recent issue of the local Product Data Sheet for the product concerned, copies of which will be supplied on request. It may be necessary to adapt the above disclaimer to specific local laws and regulations. Any changes to this disclaimer may only be implemented with permission of Sika® Corporate Legal in Baar.

Sika (NZ) Limited

85-91 Patiki Road
Avondale, Auckland 1026
New Zealand
0800 745 269
www.sika.co.nz



Product Data Sheet

SikaGrout®-212 HP NZ
January 2021, Version 03.01
020201010010000300

SikaGrout-212HPNZ-en-NZ-(01-2021)-3-1.pdf

