

PRODUCT DATA SHEET

SikaFume® SF 3263

POZZOLANIC MINERAL ADDITIVE IN SLURRY FORM

DESCRIPTION

SikaFume® SF 3263 is a modified concrete additive in liquid form based on SikaFume® Technology. It is a formulated blend of highly reactive pozzolanic materials and stabilisers designed to produce high quality concrete. SikaFume® SF 3263 is particularly suitable for chemical resistance, exposure to aggressive atmospheres, abrasion resistance and high strength mixes (in excess of 80 N/mm²). It should always be used in conjunction with a superplasticiser from the Sika range.

USES

Concrete exposed to aggressive liquids:

- Farm and food processing industries: silos, floors etc.
- Chemical industries: floors, chemical fertiliser storage etc.
- Service Stations: oils, fuels, washing areas etc.
- Sewage treatment plants: structures, sewers, etc.
- Foundations: waterproofing structures, etc.
- Sprayed concrete applications.

Concrete exposed to aggressive atmospheres:

- Marine constructions.

Concrete exposed to air pollution (urban and industrial areas).

Concrete exposed to erosion and abrasion:

- Construction of culverts – dams – concrete subject to heavy traffic or wear and tear.

FEATURES

SikaFume® SF 3263 improves properties of the fresh concrete, such as cohesion, bond and water efficiency. In hardened concrete the highly active pozzolanic material reacts with the free lime produced by the hydration of the cement to improve strength, density and durability of the concrete.

SikaFume® SF 3263 will provide the following benefits:

- Enhanced rheology
- Increased early strength
- Increased final strength
- Increased impermeability to liquids
- Increased impermeability to gases
- Reduced chloride penetration
- Reduced asr in aggregates
- Increased resistance to freeze/thaw cycle
- Increased resistance to acids
- Increased resistance to abrasion

PRODUCT INFORMATION

Packaging	IBC
Appearance and colour	Grey slurry
Shelf life	Six months from date of production
Storage conditions	Store in closed containers to prevent contamination, protect from frost. Stir and agitate the material thoroughly before use.

TECHNICAL INFORMATION

Concreting guidance	Concrete with SikaFume® SF 3263 will be subject to reduced bleed and as such vulnerable to surface water loss. Proper curing is essential.
Concrete mix design	SikaFume® SF 3263 will only enhance durability if a minimum cement con-

tent of 350 kg/m³ is used. The w/c ratio should not exceed 0.45. If necessary further dosage of Sika superplasticisers can be added. In such cases trials should always be made before full scale production is commenced. SikaFume® SF 3263 is a slurry comprising 50% water (+/-1%) and as such the water content should be included in calculated concrete water/cement ratio.

Concrete mixing time	SikaFume® SF 3263 may require additional mixing time depending upon the efficiency of the mixer used.
-----------------------------	---

APPLICATION INFORMATION

Recommended dosage	The addition rate of SikaFume® SF 3263 is generally between 5 and 30% by weight of cement. Other dosages may also be used depending on the specific working conditions. Trial mixes should be made with job materials to determine the optimum dosage required for a specified job requirement.
Compatibility	SikaFume® SF 3263 is compatible with all common cement types, contact Sika technical services for specific information.
Dispensing	SikaFume® SF 3263 is recommended to be added with the mixing water. Ensure no settlement of the SikaFume® SF 3263 has occurred during storage, thoroughly re-mix if required. Due to material density and solids content, specialist pumps are recommended for dispensing, contact your local Sika representative for additional information.

SYSTEM INFORMATION

Compatibility	SikaFume® SF 3263 is compatible with other Sika admixtures, trials are recommended to ascertain optimum dosage. Please contact Sika technical services for more information.
----------------------	--

BASIS OF PRODUCT DATA

All technical data stated in this Data Sheet are based on laboratory tests. Actual measured data may vary due to circumstances beyond our control.

ECOLOGY, HEALTH AND SAFETY

User must read the most recent corresponding Safety Data Sheets (SDS) before using any products. The SDS provides information and advice on the safe handling, storage and disposal of chemical products and contains physical, ecological, toxicological and other safety-related data.

LOCAL RESTRICTIONS

Note that as a result of specific local regulations the declared data and recommended uses for this product may vary from country to country. Consult the local Product Data Sheet for the exact product data and uses.

LEGAL NOTES

The information, and, in particular, the recommendations relating to the application and end-use of Sika products, are given in good faith based on Sika's current knowledge and experience of the products when properly stored, handled and applied under normal conditions in accordance with Sika's recommendations. In practice, the differences in materials, substrates and actual site conditions are such that no warranty in respect of merchantability or of fitness for a particular purpose, nor any liability arising out of any legal relationship whatsoever, can be inferred either from this information, or from any written recommendations, or from any other advice offered. The user of the product must test the product's suitability for the intended application and purpose. Sika reserves the right to change the properties of its products. The proprietary rights of third parties must be observed. All orders are accepted subject to our current terms of sale and delivery. Users must always refer to the most recent issue of the local Product Data Sheet for the product concerned, copies of which will be supplied on request.

Sika (NZ) Ltd
85 Patiki Road
Avondale, Auckland 1026,
New Zealand
Tel. 0800 745 269
www.sika.co.nz



Product Data Sheet
SikaFume® SF 3263
March 2025, Version 02.01
02140300000002084

SikaFumeSF3263-en-ID-(03-2025)-2-1.pdf

