

BUILDING TRUST

PRODUCT DATA SHEET

Sikafloor®-31 PurCem®

Water based polyurethane cementitious hybrid coating



DESCRIPTION

Sikafloor®-31 PurCem® is a multi-component, water-based coloured polyurethane hybrid flooring coating. It has a matt, impervious, chemical resistant, hard wearing surface.

USES

Sikafloor®-31 PurCem® is used as top and wear coat layer in Sikafloor® 21 PurCem® anti-slip system buildups and as a stand alone coating.

CHARACTERISTICS / ADVANTAGES

- Good wear resistance
- High mechanical resistance
- Good chemical resistance
- Non tainting /odourless
- VOC free
- Can be applied to substrates with high moisture content (7 days old or mature damp concrete or 10% moisture pbw)

ENVIRONMENTAL INFORMATION

Conformity with LEED v2009 IEQc 4.2: Low-Emitting Materials - Paints and Coatings

APPROVALS / STANDARDS

- Synthetic resin screed material according to EN 13813:2002, Declaration of Performance 02 08 02 02 004 0 000001 1088, certified by notified factory production control certification body 0086, certificate of conformity of the factory production control 541325, and provided with the CE marking.
- Coating for surface protection of concrete according to EN 1504-2:2004, Synthetic resin screed material according to EN 13813:2002, Declaration of Performance 02 08 02 02 004 0 000001 1088, certified by notified factory production control certification body 0086, certificate of conformity of the factory production control 541325, and provided with the CE marking.
- EN1186, EN 13130, and prCEN/TS 14234 standards, and the Decree on Consumer Goods, representing the conversion of directives 89/109/EEC, 90/128/EEC and 2002/72/EC for contact with food stuffs, according to test report by ISEGA, 32758 U11 and 32759 U11, both dated December 6th, 2011. (Tests performed on Sikafloor® -20/21/22/29 and 31 PurCem® in standard and LP versions).
- British Standards Specifications (BSS) acceptance for use in the UK.
- Campden and Chorleywood Food Research Association, Ref. S/REP/125424/1a and 2a, dated 8th February, 2012
- Fire classification report according to EN 13501-1 from Exova Warrington Fire for Sikafloor®-21 Pur-Cem® No.31050, dated 24th of March, 2012
- Liquid water transmission rate test report from the Technology Centre, Ref. 15456 dated January 25th, 2012
- Impact resistance values tested at PRA, Ref. No. 75221-151, dated January 11th, 2012

PRODUCT INFORMATION

Chemical Base	Water-based polyurethane cement hybrid			
Packaging	Part A	1.30 kg plastic bottle		
	Part B	1.50 kg plastic bottle		
	Part C	1.60 kg plastic bags		
	Pigment	0.4 kg Plastic tub		
	Part A+B+C+pigment	4.8 kg ready to mix units		
Shelf Life	Part A	12 months from date of production.		
	Part B	12 months from date of production.		
	Part C	9 months from date of production.		
Storage Conditions		The package must be stored properly in original, unopened and undamaged sealed packaging, in dry conditions at temperatures between +5 °C and +30 °C.		
Appearance / Colour	Part A	opaque liquid		
	Part B	brown liquid		
	Part C	natural grey powder		
	Available RAL colours: Contact your Sika representative for available colours			
Density	Part A+B+C mixed: ~ 1.25 kg/l ± 0.03 (at +20 °C)			
TECHNICAL INFORMATIO	N			
Shore D Hardness	~80	(ASTM D 2240		
Tensile Adhesion Strength	> 2.0 MPa (failure in concrete)	(EN 1542		
SYSTEM INFORMATION				
Systems	Please refer to the System Data Sheet of:			
	Sikafloor® PurCem® HB-21	Heavy to medium duty, broadcas-		
	Sikanoor Tareem 115 21	ted, light anti-slip hybrid screed		
	Sikafloor® PurCem® HB-22	Heavy duty broadcasted, medium anti-slip hybrid screed		
	Sikafloor® -29 PurCem®	As a coating for coving mortar		
APPLICATION INFORMAT	ION			
Mixing Ratio	Part A : P: B : C = 1 : 0.3 : 1.1 : 1. weight Mix full units only.			
Consumption	~ 0.4 – 1.0 kg/m ² (depending on	the system build-up)		
Ambient Air Temperature	+10 °C min. / +40 °C max.	+10 °C min. / +40 °C max.		
Relative Air Humidity	85 % max.			
Dew Point		The substrate and uncured floor must be at least 3 °C above dew point to reduce the risk of condensation or other disturbance of the surface on the		
Substrate Temperature	+10 °C min. / +40 °C max.			
Substrate Moisture Content	Can be installed on substrates with higher moisture content. No ponding water. Check rising moisture. The substrate needs to be visibly dry and have adequate pull-off strength min 1.5 MPa.			

Product Data Sheet Sikafloor®-31 PurCem® December 2023, Version 05.02 020814020030000003



Pot Life	Temperatures	Time	e	
	+10 °C	~ 35	–40 minutes	
	+20 °C	~ 22	~ 22–25 minutes	
	+30 °C	~ 15	~ 15–18 minutes	
	+35 °C	~ 12	~ 12–15 minutes	
Curing Time	Before overcoating Sikafloor®-31 PurCem® allow:			
	Substrate temperature	Minimum	Maximum	
	+10 °C	16 hours	72 hours	
	+20 °C	8 hours	48 hours	
	+30 °C	4 hours	24 hours	
	+35 °C	4 hours	24 hours	

BASIS OF PRODUCT DATA

All technical data stated in this Product Data Sheet are based on laboratory tests. Actual measured data may vary due to circumstances beyond our control.

FURTHER DOCUMENTS

- Sikafloor® PurCem® Method Statement
- Sika® Method Statement Mixing and Application of Flooring Systems
- Sika® Method Statement Surface Evaluation & Preparation
- Sikafloor® PurCem® System Data Sheets

LIMITATIONS

- Do not apply to PCC (polymer modified cement mortars) that may expand due to moisture when sealed with an impervious resin.
- Always ensure good ventilation when using Sikafloor®-31 PurCem® in a confined space, to prevent excessive ambient humidity.
- Freshly applied Sikafloor®-31 PurCem®, must be protected from damp, condensation and direct water contact (rain) for at least 24 hours.
- Protect the substrate during application from condensation from pipes or any overhead leaks.
- Do not apply to cracked or unsound substrates.
- Always allow a minimum of 48 hours after product application prior to placing into service in proximity with food stuffs.
- Products of the Sikafloor® PurCem® product range are subject to discolouration when exposed to UV radiation. Extend depends on colour. There are no measurable losses of any properties when this occurs and it is a purely aesthetical matter. Products can be used outside provided the change in appearance is acceptable by the customer.
- In some slow curing conditions, soiling of the surface may occur when opened to foot traffic, even though mechanical properties have been achieved. It is advised to remove dirt using a dry mop or cloth. Avoid scrubbing with water for the first three days.

ECOLOGY HEALTH AND SAFETY

For information and advice on the safe handling, storage and disposal of chemical products, users shall refer to the most recent Safety Data Sheet (SDS) containing physical, ecological, toxicological and other safety-related data.

APPLICATION INSTRUCTIONS

SUBSTRATE QUALITY / PRE-TREATMENT

The surface must be clean, dry and free of all contaminants such as dirt, oil, grease, coatings and surface treatments, etc. All dust, loose and friable material must be completely removed from all surfaces before application of the product, preferably by vacuum. Pull off strength shall not be less than 1.5 N/mm². If in doubt apply a test area first.

MIXING

Premix part A with a low speed electric stirrer and then add pigment and mix until uniform. Add part B and mix for 30 seconds, until a uniform colour is achieved

Use a double paddle (axis) mixer and gradually add part C (aggregate) to the mixed resin. Allow part C to blend for further 2 minutes minimum, to ensure complete mixing and a uniform moist mix is obtained. During the operations, scrape down the sides and bottom of the container with a flat or straight edge trowel at least once (parts A+P+B+C) to ensure complete mixing. **Mixing Tools**

A low speed electric stirrer (300-400 r.p.m.) and an Exomixer-type mixing paddle suited to the size of the mixing container to minimise the air entrapment.



APPLICATION

On smooth screeds apply the mixed Sikafloor®-31 Pur-Cem® using a short or medium nap roller directly from a paint tray. On broadcasted screeds pour the material and spread it using a squeegee and then back-roll the excess using a medium knap roller.

CLEANING OF TOOLS

Clean all tools and application equipment with Sika® Thinner C immediately after use. Hardened / cured material can only be mechanically removed.

LOCAL RESTRICTIONS

Please note that as a result of specific local regulations the performance of this product may vary from country to country. Please consult the local Product Data Sheet for the exact description of the application fields.

LEGAL NOTES

The information, and, in particular, the recommendations relating to the application and end-use of Sika products, are given in good faith based on Sika's current knowledge and experience of the products when properly stored, handled and applied under normal conditions in accordance with Sika's recommendations. In practice, the differences in materials, substrates and actual site conditions are such that no warranty in respect of merchantability or of fitness for a particular purpose, nor any liability arising out of any legal relationship whatsoever, can be inferred either from this information, or from any written recommendations, or from any other advice offered. The user of the product must test the product's suitability for the intended application and purpose. Sika reserves the right to change the properties of its products. The proprietary rights of third parties must be observed. All orders are accepted subject to our current terms of sale and delivery. Users must always refer to the most recent issue of the local Product Data Sheet for the product concerned, copies of which will be supplied on request. It may be necessary to adapt the above disclaimer to specific local laws and regulations. Any changes to this disclaimer may only be implemented with permission of Sika® Corporate Legal in Baar.

Sika (NZ) Limited

85-91 Patiki Road Avondale, Auckland 1026 New Zealand 0800 745 269 www.sika.co.nz





Product Data Sheet
Sikafloor®-31 PurCem®
December 2023, Version 05.02
020814020030000003



