

PRODUCT DATA SHEET

Sika® Sigunit® L-5650 AF

Alkali free liquid shotcrete accelerator

DESCRIPTION

Sika® Sigunit® L-5650 AF is a high-performance alkali free liquid set accelerator for shotcrete, providing high early strength development and good substrate adhesion.

USES

Sika® Sigunit® L-5650 AF is suitable for both dry and wet spraying processes and it is used for:

- Excavation stabilisation in tunnelling and mining
- Rock, slope and trench stabilisation
- High quality shotcrete lining

FEATURES

- High early strength development
- Alkali-free
- Minimal strength loss of the accelerated concrete
- No pollution of groundwater by leached out alkalis
- Reduced rebound and dust
- Improved adhesion of shotcrete to the substrate
- Chloride-free (does not induce reinforcement corrosion)

PRODUCT INFORMATION

Composition	Inorganic aluminium complexes
Packaging	IBC or Bulk Refer to current price list for packaging variations
Shelf life	3 months from date of production
Storage conditions	Product must be stored in original, unopened and undamaged sealed packaging in dry conditions at temperatures between +5 °C and +35 °C. Always refer to packaging / labelling. Use clean containers when delivered in bulk. If separation of Sika® Sigunit® L-5650 AF occurs, the suspension must be completely mixed before using. Do not store in standard steel containers.
Appearance and colour	light beige suspension
Density	~1.51 kg/l
Conventional dry material content	~55 %
Viscosity	≤ 500 mPas at 20 °C
pH-Value	~2,5
Total chloride ion content	≤ 0,1 %
Equivalent sodium oxide	≤ 1,0 %

PRODUCT DATA SHEET

Sika® Sigunit® L-5650 AF

August 2024, Version 01.01

021401011000000226

TECHNICAL INFORMATION

Specific advice	Sika® Sigunit® L-5650 AF is added at the nozzle. Accurate and constant dosing into the concrete flow is essential.
Concrete mix design	The suitability of the proposed mix design must be tested in field trials before commencement of the project. High quality shotcrete requires a w/c ratio of less than 0,5 and a flow table spread of more than 500 mm. Temperature of basic mix must be higher than 15 °C.
Substrate	The substrate must be clean, free of loose stones and free of water under hydrostatic pressure.

APPLICATION INFORMATION

Recommended dosage	The correct dosage must be determined by preliminary testing. For layer thicknesses of up to 10 cm applied in one pass, the recommended accelerator dosage is between 4 % and 9 % by weight of binder. Lower ambient and basic mix temperatures require higher dosage of accelerator.
--------------------	---

BASIS OF PRODUCT DATA

All technical data stated in this Data Sheet are based on laboratory tests. Actual measured data may vary due to circumstances beyond our control.

IMPORTANT CONSIDERATIONS

- The accelerator's effect depends on the content, age and type of cement, as well as on the shotcrete temperature.
- Shotcrete quality is widely affected by the substrate, the applied layer thickness, the spraying process, the quality of equipment and the application technique.
- The w/c ratio of the basic concrete mix in the wet spraying process, and the quantity of gauging water in the dry spraying process are also parameters influencing the acceleration effect of Sika® Sigunit® L-5650 AF.
- When using sulphate resistant cements strength development can be slower.
- Sika® Sigunit® L-5650 AF is not compatible with alkaline shotcrete accelerators.
- Before using Sika® Sigunit® L-5650 AF the accelerator hoses must be cleaned thoroughly.
- The use of Sika® Sigunit® L-5650 AF requires technically correct dosing and conveying / spraying technology.
- Metal parts of the pump and piping that come into direct contact with Sika® Sigunit® L-5650 AF must be made of stainless steel.
- Contact your local Sika Company for any additional technical support.

ECOLOGY, HEALTH AND SAFETY

User must read the most recent corresponding Safety Data Sheets (SDS) before using any products. The SDS provides information and advice on the safe handling, storage and disposal of chemical products and contains physical, ecological, toxicological and other safety-related data.



PRODUCT DATA SHEET
Sika® Sigunit® L-5650 AF
August 2024, Version 01.01
021401011000000226

LOCAL RESTRICTIONS

Note that as a result of specific local regulations the declared data and recommended uses for this product may vary from country to country. Consult the local Product Data Sheet for exact product data and uses.

LEGAL NOTES

The information, and, in particular, the recommendations relating to the application and end-use of Sika products, are given in good faith based on Sika's current knowledge and experience of the products when properly stored, handled and applied under normal conditions in accordance with Sika's recommendations. In practice, the differences in materials, substrates and actual site conditions are such that no warranty in respect of merchantability or of fitness for a particular purpose, nor any liability arising out of any legal relationship whatsoever, can be inferred either from this information, or from any written recommendations, or from any other advice offered. The user of the product must test the product's suitability for the intended application and purpose. Sika reserves the right to change the properties of its products. The proprietary rights of third parties must be observed. All orders are accepted subject to our current terms of sale and delivery. Users must always refer to the most recent issue of the local Product Data Sheet for the product concerned, copies of which will be supplied on request.

SikaSigunitL-5650AF-en-MN-(08-2024)-1-1.pdf