

PRODUCT DATA SHEET

Sarnafil® G 410-20 L

Polymeric PVC detailing membrane for roof waterproofing



SIKA NZ
APPROVED
CONTRACTOR
ONLY

DESCRIPTION

Sarnafil® G 410-20 L (thickness 2.0 mm) is a multi-layer, synthetic roof waterproofing sheet based on polyvinyl chloride (PVC) with a glass non-woven inlay. It contains ultraviolet light stabilisers according to EN 13956 / GB 12952. Sarnafil® G 410-20 L is a hot-air weldable roof membrane, formulated for direct exposure and designed for use in all global climatic conditions.

USES

Sarnafil® G 410-20 L may only be used by experienced professionals.

Detailing membrane for the following Sarnafil system membranes:

- Sarnafil® S 327 L
- Sarnafil® G 410 L Felt

Roof waterproofing membrane for garden/green roofs

CHARACTERISTICS / ADVANTAGES

- Proven performance over decades
- Lacquer coated surface
- Resistant to permanent UV exposure
- High dimensional stability from glass fleece inlay
- High water vapour permeability
- Resistant to all common environmental influences
- Resistant to micro-organisms
- Resistant to root penetration
- Hot-air weldable
- No open flame equipment required

ENVIRONMENTAL INFORMATION

- Conformity with LEED v4 MRc 3 (Option 2): Building Product Disclosure and Optimization - Sourcing of Raw Materials
- Conformity with LEED v4 MRc 4 (Option 2): Building Product Disclosure and Optimization - Material Ingredients

APPROVALS / STANDARDS

- CE Marking and Declaration of Performance to EN 13956 - Polymeric sheets for roof waterproofing
- GB 12952, Sarnafil® G 410-20 L, Test report No. RS19-21
- Included in BRANZ appraisal #619, Sarnafil Roof and Deck Membrane System, as detailing membrane
- BRANZ appraisal #902, Sarnafil Green Roof Waterproofing System, as complete membrane solution
- FLL standard, 2008 - Method of testing resistance to root damage to flexible sheets and coatings for roof planting

PRODUCT INFORMATION

Product Declaration	EN 13956: Polymeric sheets for roof waterproofing GB 12952 - Type G	
Chemical Base	Polyvinyl Chloride (PVC)	
Packaging	Standard rolls are wrapped individually in a blue PE-foil. Packing unit Refer to price list Roll length 15.00 m Roll widths 0.2 m, 2.00 m Roll weights 0.2 m = 8.1 kg, 2.00 m = 81 kg Refer to current price list for packaging variations.	
Shelf Life	5 years from date of production.	
Storage Conditions	Product must be stored in original unopened and undamaged packaging in dry conditions and temperatures between +5 °C and +30 °C. Store in a horizontal position. Do not stack pallets of the rolls on top of each other, or under pallets of any other materials during transport or storage. Always refer to packaging.	
Appearance / Colour	Surface	matt
	Colours	
	Top Surface	light grey (other colours on request)
	Bottom surface	dark grey
Visible Defects	Pass	(EN 1850-2)
Length	15 m (-0 / +5 %)	(EN 1848-2)
Width	2 m (-0,5 / +1 %)	(EN 1848-2)
Effective Thickness	2.0 mm (-5 / +10 %)	(EN 1849-2)
Overall Thickness	2.0 mm (-5 % / +10 %)	(GB 12952)
Straightness	≤ 30 mm	(EN 1848-2)
Flatness	≤ 10 mm	(EN 1848-2)
Mass per Unit Area	2.57 kg/m ² (-5 / +10 %)	(EN 1849-2)

SYSTEM INFORMATION

System Structure	The following products must be considered for use depending on roof design: <ul style="list-style-type: none">▪ Sarnafil® Metal Sheet▪ Sarnabar®▪ Sarnacol® 2170 (contact adhesive)▪ Sarnacol® 2152 (2-component polyurethane adhesive) Ancillary products: wide range of accessories is available e.g. prefabricated parts, roof drains, scuppers, walkway pads and decor profiles
Compatibility	Not compatible in direct contact with bitumen, tar, fat, oil, solvent containing materials and other plastic materials. Must be isolated from contact with building wrap systems (including building wraps with self-adhesive backings) and flashing tapes. Refer to Sika for detailing advice. Insulated boards of expanded polystyrene (EPS), extruded polystyrene (XPS), polyurethane (PUR), polyisocyanurate (PIR) or phenolic foam (PF) should be isolated from the membrane either with integral aluminium or glass tissue facers, or with separation cloth such as Sarnafil S-Felt. Direct contact with any of the above materials could adversely affect the product properties.

TECHNICAL INFORMATION

Resistance to Impact	hard substrate	≥ 800 mm	(EN 12691)
	soft substrate	≥ 1250 mm	
	watertight		(GB/T20624.2)
Resistance to Static Load	soft substrate	≥ 20 kg	(EN 12730)
	rigid substrate	≥ 20 kg	
	watertight		(GB/T328.25)
Resistance to Root Penetration	Pass		(EN 13948)
Tensile Strength	longitudinal (md) ¹⁾	≥ 8.5 N/mm ²	(EN 12311-2)
	transversal (cmd) ²⁾	≥ 8.5 N/mm ²	
	longitudinal (md) ¹⁾	≥ 10 MPa	(GB/T328.9)
	transversal (cmd) ²⁾	≥ 10 MPa	
	¹⁾ md = machine direction		
	²⁾ cmd = cross machine direction		
Elongation at Break	≥ 200 %		(GB/T328.9)
Elongation	longitudinal (md) ¹⁾	≥ 180 %	(EN 12311-2)
	transversal (cmd) ²⁾	≥ 180 %	
	¹⁾ md = machine direction		
	²⁾ cmd = cross machine direction		
Tear Strength	≥ 50 N/mm		(GB/T529)
Joint Peel Resistance	Failure mode: C, no failure of the joint		(EN 12316-2)
	≥ 3 N/mm		(GB/T328.21)
Dimensional Stability	longitudinal (md) ¹⁾	$\leq 0.2 $ %	(EN 1107-2)
	transversal (cmd) ²⁾	$\leq 0.1 $ %	
		$\leq 0,1$ %	(GB/T328.13)
	¹⁾ md = machine direction		
	²⁾ cmd = cross machine direction		
Solar Reflectance	0,80		(GJB 2502.2)
Solar Reflectance Index	106 (white, initial)		(ASTM E 1980)
Foldability at Low Temperature	≤ -25 °C		(EN 495-5)
	no crack		(GB/T328.15)
Water Absorption	wet weight	≤ 4 %	(GB 12952)
	dry weight	≥ -0.4 %	
Water Tightness	Pass		(EN 19289)
	watertight		(GB/T328.10)
Water Vapour Transimission	$\mu = 15$ 000		(EN 1931)
Resistance to UV Exposure	Pass (> 5 000 h / grade 0)		(EN 1297)
Resistance to Weathering	tensile strength retention	≥ 85 %	(GB/T18244)
	elongation retention	≥ 90 %	
	low temperature bend	no crack	
Retention of Properties after Heat Ageing	tensile strength retention	≥ 85 %	(GB/T18244)
	elongation retention	≥ 80 %	
	low temperature bend	no crack	

APPLICATION INFORMATION

Ambient Air Temperature	-20 °C min. / +60 °C max.
Substrate Temperature	-30 °C min. / +60 °C max.

BASIS OF PRODUCT DATA

All technical data stated in this Product Data Sheet are based on laboratory tests. Actual measured data may vary due to circumstances beyond our control.

FURTHER DOCUMENTS

Installation

- Application Manual

LIMITATIONS

Installation work must only be carried out by Sika® trained and approved contractors experienced in this type of application.

- Ensure Sarnafil® G 410-20 L is prevented from direct contact with incompatible materials (refer to compatibility section).
- Do not apply to wet, damp or unclean surfaces
- The use of some ancillary products such as adhesives, cleaners and solvents is limited to temperatures above +5 °C. Observe temperature limitations in the appropriate Product Data Sheets.
- Special measures may be compulsory for installation below +5 °C ambient temperature due to safety requirements in accordance with national regulations.

ECOLOGY HEALTH AND SAFETY

Fresh air ventilation must be ensured, when working (welding) in closed rooms. Installation of RAL 9016 SR type requires the use of UV protection goggles.

REGULATION (EC) NO 1907/2006 - REACH

This product is an article as defined in article 3 of regulation (EC) No 1907/2006 (REACH). It contains no substances which are intended to be released from the article under normal or reasonably foreseeable conditions of use. A safety data sheet following article 31 of the same regulation is not needed to bring the product to the market, to transport or to use it. For safe use follow the instructions given in this product data sheet. Based on our current knowledge, this product does not contain SVHC (substances of very high concern) as listed in Annex XIV of the REACH regulation or on the candidate list published by the European Chemicals Agency in concentrations above 0.1 % (w/w)

APPLICATION INSTRUCTIONS

EQUIPMENT

Hot welding overlap seams

Electric hot-air welding equipment, such as hand held manual hot air welding equipment and pressure rollers or automatic hot air welding machines with controlled hot-air temperature capability of a minimum +600 °C.

Recommended type of equipment:

- Manual: Leister Triac
- Automatic: Leister Varimat

SUBSTRATE QUALITY

The substrate surface must be uniform, smooth and free of any sharp protrusions or burrs, etc. Sarnafil® G 410-20 L must be separated from any incompatible substrates / materials by an effective separation layer to prevent accelerated ageing. The supporting layer must be compatible with the membrane, solvent resistant, clean, dry and free of grease and dust. Metal sheets must be degreased with Sarna Cleaner before adhesive is applied.

APPLICATION

Installation procedure

Strictly follow installation procedures as defined in method statements, application manuals and working instructions which must always be adjusted to the actual site conditions.

Flashings

Refer to standard details in Application Manual

Hot welding overlap seams

Overlap seams must be welded by electric hot welding equipment. Welding parameters including temperature, machine speed, air flow, pressure and machine settings must be evaluated, adapted and checked on site according to the type of equipment and the climatic conditions prior to welding. The effective width of welded overlaps by hot-air must be a minimum 20 mm.

Testing overlap seams

The seams must be mechanically tested with a screwdriver (rounded edges) to ensure the integrity/completion of the weld. Any imperfections must be rectified by hot air welding.

LOCAL RESTRICTIONS

Please note that as a result of specific local regulations the performance of this product may vary from coun-

try to country. Please consult the local Product Data Sheet for the exact description of the application fields.

LEGAL NOTES

The information, and, in particular, the recommendations relating to the application and end-use of Sika products, are given in good faith based on Sika's current knowledge and experience of the products when properly stored, handled and applied under normal conditions in accordance with Sika's recommendations. In practice, the differences in materials, substrates and actual site conditions are such that no warranty in respect of merchantability or of fitness for a particular purpose, nor any liability arising out of any legal relationship whatsoever, can be inferred either from this information, or from any written recommendations, or from any other advice offered. The user of the product must test the product's suitability for the intended application and purpose. Sika reserves the right to change the properties of its products. The proprietary rights of third parties must be observed. All orders are accepted subject to our current terms of sale and delivery. Users must always refer to the most recent issue of the local Product Data Sheet for the product concerned, copies of which will be supplied on request. It may be necessary to adapt the above disclaimer to specific local laws and regulations. Any changes to this disclaimer may only be implemented with permission of Sika® Corporate Legal in Baar.

Sika (NZ) Limited

85-91 Patiki Road
Avondale, Auckland 1026
New Zealand
0800 745 269
www.sika.co.nz



Product Data Sheet
Sarnafil® G 410-20 L
December 2023, Version 01.03
020905032000205003

SarnafilG410-20L-en-NZ-(12-2023)-1-3.pdf

