

PRODUCT DATA SHEET

Sikalastic®-701

Aliphatic polyurethane hybrid top coat for liquid-applied membrane waterproofing systems

AVAILABLE
ON INDENT
ORDER
ONLY

SIKA NZ
APPROVED
CONTRACTOR
ONLY

DESCRIPTION

Sikalastic®-701 is a 2-part, hybrid, gloss-finish polyurethane top coat for Sika® Liquid Applied Membrane waterproofing systems.

USES

Sikalastic®-701 is used as a gloss-finish top coat for:

- Sikalastic®-625 liquid-applied membrane systems
- Sikalastic®-701 is used for the following waterproofing applications:
- Newly applied membranes or for renovating existing membranes
 - Flat and sloped roofs
 - Walkways
 - Terraces
 - Podium decks

Please note:

- The Product may only be used by experienced professionals.
- The Product may only be used for exterior applications.

CHARACTERISTICS / ADVANTAGES

- Good yellowing resistance provides long-term colour stability
- Very good resistance to weathering
- Good gloss retention
- Good resistance to specific chemicals
- Low surface soiling
- Easy to clean and low maintenance
- Very good solar reflectance making it suitable for cool roofs
- Resistant to ponding water

APPROVALS / STANDARDS

- Fire Testing EN 13501-5, Sikalastic®-701, Sikalastic®-702, Warringtonfire, Repor
- Abrasion resistance ARO.5(Special), Sikalastic®-614/701, FACE, Test report No. F
- CE marking and declaration of performance based on European Technical Assessment ETA-20/1013. ETA issued on the basis of EAD 030350-00-0402 Liquid applied roof waterproofing kits.

PRODUCT INFORMATION

Chemical Base	Aliphatic polyurethane hybrid	
Packaging	Container Part A	10 kg
	Container Part B	2.5 kg
	Container Part A + Part B	12.5 kg
	Refer to Sika NZ for available packaging variations.	
Colour	Cured colour	White
	Refer to Sika NZ for other colour options.	
Shelf Life	Part A	24 months from date of production
	Part B	12 months from date of production
Storage Conditions	The Product must be stored in original, unopened and undamaged sealed	

packaging in dry conditions at temperatures between +5 °C and +30 °C. Always refer to packaging.

Refer to the current Safety Data Sheet for information on safe handling and storage.

Density	Mixed Product	1.25 kg/l	(EN ISO 2811-1)
	For colours other than white, light grey and dark grey, values may vary. Contact Sika NZ for further advice.		
Solid content by weight	Part A	67 %	
	Part B	100 %	
For colours other than white, light grey and dark grey, values may vary. Contact Sika Technical Services for further advice.			
Solid content by volume	Part A	55 %	
	Part B	100 %	
For colours other than white, light grey and dark grey, values may vary. Contact Sika Technical Services for further advice.			

TECHNICAL INFORMATION

Tensile Strength	Tested at +23 °C	10 MPa	(EN ISO 527-3)
	Tested at -20 °C	20 MPa	
Elongation at Break	Tested at +23 °C	100 %	(EN ISO 527-3)
	Tested at -20 °C	20 %	
External Fire Performance	B _{roof} (T1)		(CEN/TS 1187)
	B _{roof} (T4)		
Reaction to Fire	Class E		(EN 13501-1)
Chemical Resistance	Resistant to many chemicals. Contact Sika NZ for specific information.		
Solar Reflectance	Initial	0.88	(ASTM C1549)
Thermal Emittance	Initial	0.86	(ASTM C1371-15)
Solar Reflectance Index	Initial (Convective coefficient, medium wind)	112	(ASTM E1980)

APPLICATION INFORMATION

Mixing Ratio	Part A : Part B (by volume)	80 : 20	
Consumption	0.25–0.35 kg/m ² applied in a single coat For colours other than white, light grey and dark grey, values may vary. Contact Sika NZ for further advice.		
Product Temperature	Maximum	+40 °C	
	Minimum	+2 °C	
Ambient Air Temperature	Maximum	+40 °C	
	Minimum	+2 °C	
Relative Air Humidity	Temperature	Minimum	Maximum
	Above +20 °C	35 %	80 %
	Below +20 °C	45 %	80 %
Dew Point	Beware of condensation. Substrate temperature during application must be at least +3 °C above dew point.		

Substrate Temperature	Maximum	+40 °C		
	Minimum	+2 °C		
Substrate Moisture Content	Refer to the individual Product Data Sheet.			
Pot Life	+20 °C	1 hour		
Tack Free Time	Tested at +20 °C and 50 % RH:			
	Tack free time	45 minutes		
	Hard drying time	60 minutes		
	Dry to touch	90 minutes		
	Tested at +5 °C and 50 % RH:			
	Tack free time	75 minutes		
	Hard drying time	105 minutes		
	Dry to touch	135 minutes		
	Note: Times are approximate and will be affected by changing ambient conditions, particularly temperature and relative humidity.			
	Applied Product Ready for Use	Curing conditions	Rain resistant	Foot traffic
+10 °C and 50 % RH		75 minutes	150 minutes	1 day
+20 °C and 50 % RH		60 minutes	120 minutes	1 day
+30 °C and 50 % RH		45 minutes	90 minutes	16 hours
Note: Times are approximate and will be affected by changing ambient conditions, particularly temperature and relative humidity.				

SYSTEM INFORMATION

System Structure	Sikalastic®-701 can be used with the following: 1-Part PU cold applied systems ▪ Sikalastic®-625 N
-------------------------	--

BASIS OF PRODUCT DATA

All technical data stated in this Product Data Sheet are based on laboratory tests. Actual measured data may vary due to circumstances beyond our control.

ECOLOGY HEALTH AND SAFETY

For information and advice on the safe handling, storage and disposal of chemical products, users shall refer to the most recent Safety Data Sheet (SDS) containing physical, ecological, toxicological and other safety-related data.

APPLICATION INSTRUCTIONS

SUBSTRATE PREPARATION

Preconditions

Confirm waiting time to overcoating has been achieved for the previously applied system base layer.

1. If the maximum overcoating time of the base layer is exceeded, prepare the surface of the existing coating using Sika Reactivation Primer®. Contact Sika NZ for advice.
2. Remove dust and contamination from the prepared

surface using vacuum extraction equipment.

MIXING

IMPORTANT

Do not dilute with solvent or water.

TOP COAT MIXING PROCEDURE

1. Mix Part A (resin) until the coloured pigment is dispersed and a uniform colour is achieved.
2. Add Part B (hardener) to Part A.
3. IMPORTANT Do not mix excessively. Mix Part A + B continuously for ~3 minutes, using an electric drill (min. 300 rpm) until a uniformly coloured mix is achieved.
4. To ensure thorough mixing, pour materials into another container and mix again to achieve a smooth and uniform mix.
5. During the final mixing stage, scrape down the sides and bottom of the mixing container with a flat or straight edge trowel at least once to ensure complete mixing.

APPLICATION

IMPORTANT

Application by trained personnel

The application of this Product must only be carried out by an applicator that is trained or approved by

Sika. The applicator must also be experienced in this type of application.

IMPORTANT

Risk of fumes entering air conditioning units

Do not apply close to running air conditioning unit intake vents. Switch off units and seal intakes before applying.

1. Apply the Product in one coat by roller, brush or spray equipment to achieve a consistent thickness and required surface finish.

CLEANING OF TOOLS

Clean all tools and application equipment with water immediately after use. Hardened material can only be removed mechanically.

LOCAL RESTRICTIONS

Please note that as a result of specific local regulations the performance of this product may vary from country to country. Please consult the local Product Data Sheet for the exact description of the application fields.

LEGAL NOTES

The information, and, in particular, the recommendations relating to the application and end-use of Sika products, are given in good faith based on Sika's current knowledge and experience of the products when properly stored, handled and applied under normal conditions in accordance with Sika's recommendations. In practice, the differences in materials, substrates and actual site conditions are such that no warranty in respect of merchantability or of fitness for a particular purpose, nor any liability arising out of any legal relationship whatsoever, can be inferred either from this information, or from any written recommendations, or from any other advice offered. The user of the product must test the product's suitability for the intended application and purpose. Sika reserves the right to change the properties of its products. The proprietary rights of third parties must be observed. All orders are accepted subject to our current terms of sale and delivery. Users must always refer to the most recent issue of the local Product Data Sheet for the product concerned, copies of which will be supplied on request. It may be necessary to adapt the above disclaimer to specific local laws and regulations. Any changes to this disclaimer may only be implemented with permission of Sika® Corporate Legal in Baar.

Sika (NZ) Limited

85-91 Patiki Road
Avondale, Auckland 1026
New Zealand
0800 745 269
www.sika.co.nz



Product Data Sheet

Sikalastic®-701

November 2024, Version 03.05
020915505000000013