

PRODUCT DATA SHEET

Sika® Plastiment® BV-40 N

WATER REDUCING CONCRETE ADMIXTURE

DESCRIPTION

Sika® Plastiment® BV-40 N is an admixture designed for use in concrete to allow increased workability and water reduction to be achieved.

USES

- Sika® Plastiment® BV-40 N is used to produce workable concrete with a lower total water content and should be considered wherever high quality concrete is required
- Sika® Plastiment® BV-40 N can be used with all grades of concrete

CHARACTERISTICS / ADVANTAGES

Mixes designed incorporating Sika® Plastiment® BV-40 N can show economies through cement reduction, whilst still improving the plastic and hardened properties of the concrete. Using Sika® Plastiment® BV-40 N results in a reduction in batching water without loss of workability.

Typical performance advantages are:

- Increased strength and long term durability properties
- Reduced long term shrinkage and creep
- Improved surface finish
- Placing in difficult situations is made easier
- Improved characteristics of concrete with difficult and harsh aggregate or sands

APPROVALS / STANDARDS

Meets the physical requirements of NZS 3113

PRODUCT INFORMATION

Chemical Base	Liquid based on modified ligno sulphonate
Packaging	200 litre drums and bulk delivery
Appearance / Colour	Brown liquid
Shelf Life	Twelve (12) months from date of manufacture when stored as stated.
Storage Conditions	Store in unopened, original containers free from frost and at temperatures between +5°C and +35°C.
Specific Gravity	~ 1.18 kg/litre
Total Chloride Ion Content	Nil

TECHNICAL INFORMATION

Concreting Guidance	Air entrainment: ~ 1.0% Water reduction: Yes Freezing point: -5°C Suitable for all type of Portland cements, including sulphate resistant ce-
---------------------	--

ment.

Specific Advice

Higher dosages will retard setting time.

APPLICATION INFORMATION

Recommended Dosage

200 ml - 500 ml. Trial mixes are recommended to establish exact dosage rates required to suit individual requirements. If assistance is required please contact Sika.

Compatibility

Sika® Plastiment® BV-40 N is compatible with other Sika admixtures, but add separately - do not premix.

APPLICATION INSTRUCTIONS

LIMITATIONS

- If accidental overdosing of Sika® Plastiment® BV-40 N occurs, the setting times will be retarded. During this period the concrete must be kept moist to prevent premature drying out
- As with all concrete and mortars, it is essential to protect mixes containing Sika® Plastiment® BV-40 N from water evaporation during the crucial early age curing period. We recommend the use of Sika Antisol curing membranes for this purpose. Refer to the Sika Antisol A or E data sheet for further information.
- To avoid moisture evaporation from the concrete surface during the finishing period Sika recommend the use of Sika® Film (refer to Sika® Film data sheet)
- When using Sika® Plastiment® BV-40 N in concrete containing air entraining admixture, dosages of the latter may need to be reduced to maintain the same target level of air entrainment

BASIS OF PRODUCT DATA

All technical data stated in this Product Data Sheet are based on laboratory tests. Actual measured data may vary due to circumstances beyond our control.

LOCAL RESTRICTIONS

Please note that as a result of specific local regulations the performance of this product may vary from country to country. Please consult the local Product Data Sheet for the exact description of the application fields.

ECOLOGY HEALTH AND SAFETY

For information and advice on the safe handling, storage and disposal of chemical products, users shall refer to the most recent Safety Data Sheet (SDS) containing physical, ecological, toxicological and other safety-related data.

LEGAL NOTES

The information, and, in particular, the recommendations relating to the application and end-use of Sika products, are given in good faith based on Sika's current knowledge and experience of the products when properly stored, handled and applied under normal conditions in accordance with Sika's recommendations. In practice, the differences in materials, substrates and actual site conditions are such that no warranty in respect of merchantability or of fitness for a particular purpose, nor any liability arising out of any legal relationship whatsoever, can be inferred either from this information, or from any written recommendations, or from any other advice offered. The user of the product must test the product's suitability for the intended application and purpose. Sika reserves the right to change the properties of its products. The proprietary rights of third parties must be observed. All orders are accepted subject to our current terms of sale and delivery. Users must always refer to the most recent issue of the local Product Data Sheet for the product concerned, copies of which will be supplied on request. It may be necessary to adapt the above disclaimer to specific local laws and regulations. Any changes to this disclaimer may only be implemented with permission of Sika® Corporate Legal in Baar.

Sika (NZ) Limited

85-91 Patiki Road
Avondale, Auckland 1026
New Zealand
0800 745 269
www.sika.co.nz

**Product Data Sheet**

Sika® Plastiment® BV-40 N
December 2019, Version 02.01
02130301100000107

SikaPlastimentBV-40N-en-NZ-(12-2019)-2-1.pdf

