

BUILDING TRUST

BUILDING PRODUCT INFORMATION SHEET Sarnafil® G 410-20 L Felt

Polymeric membrane for adhered roof waterproofing

DESCRIPTION

Sarnafil[®] G 410-20 L Felt (thickness 2.0 mm) is a multi-layer, synthetic roof waterproofing sheet based on polyvinyl chloride (PVC) with a glass non-woven inlay and polyester fleece backing. It contains ultraviolet light stabilisers according to EN 13956 / GB 12952. Sarnafil[®] G 410-20 L Felt is a hot-air weldable roof membrane, formulated for direct exposure and designed for use in all global climatic conditions.

USES

Sarnafil[®] G 410-20 L Felt may only be used by experienced professionals.

Waterproofing membrane for:

Fully bonded, exposed roofs

FEATURES

- Proven performance over decades
- Lacquer coated surface
- Resistant to permanent UV exposure
- Fast installation with Sarnacol[®] adhesives
- High dimensional stability from glass fleece inlay

PRODUCT INFORMATION

- High water vapour permeability
- Resistant to all common environmental influences
- Hot-air weldable
- No open flame equipment required

SUSTAINABILITY

- Conformity with LEED v4 MRc 3 (Option 2): Building Product Disclosure and Optimization - Sourcing of Raw Materials
- Conformity with LEED v4 MRc 4 (Option 2): Building Product Disclosure and Optimization - Material Ingredients

LIMITATIONS OF USE

The installation of Sarnafil Membrane systems is complex and limited to Sika approved applicators only. The Sika technical literature should be referred to in all instances for the correct application procedures nzl.sika.com

APPROVALS / CERTIFICATES

- CE Marking and Declaration of Performance to EN 13956 -Polymeric sheets for roof waterproofing
- GB 12952, Sarnafil® G 410-20 L Felt, Test report No. RS19-21

Product identifier	Sarnafil® G 410-20 L Felt		
Place of manufacture	Overseas		
Product declaration	EN 13956 - Polymeric sheets for roof waterproofing		
	GB 12952 - Type GL		
Composition	Polyvinyl Chloride (PVC)		
Packaging	Standard rolls are wrapped individually in a blue PE-foil. Roll size		
	Length	15.00 m	
	Width	2.00 m	
	Weight	84.00 kg	

NZ BUILDING PRODUCT INFORMATION SHEET

Sarnafil® G 410-20 L Felt 12/12/2024 File version 1.0 020905052150205003

	Refer to current price list for packaging variations.				
Shelf life	5 years from date of production.				
Storage conditions	Product must be stored in original unopened and undamaged packaging in dry conditions and tem- peratures between +5 °C and +30 °C. Store in a horizontal position. Do not stack pallets of the rolls on top of each other, or under pallets of any other materials during transport or storage. Always refer to packaging.				
Appearance and colour	Surface		matt		
	Colours				
	Top Surface		light grey		
	Bottom surface		dark grey		
	Top surface colour available in other colours subject to minimum order quantities.				
Visible defects	Pass		(EN 1850-2)	(EN 1850-2)	
Length	15.00 m (-0 / +5 %)		(EN 1848-2)		
Width	2.00 m (-0.5 / +1%)		(EN 1848-2)	(EN 1848-2)	
Effective thickness	2.0 mm (-5 / +10 %)		(EN 1849-2)	(EN 1849-2)	
Overall thickness	2.0 mm (-5 / +10 %)		(GB 12952)		
Straightness	≤ 30 mm		(EN 1848-2)		
Flatness	≤ 10 mm		(EN 1848-2)		
Mass per area	2.75 kg/m ² (-5 / +10 %)		(EN 1849-2)		
TECHNICAL INFORMA	TION				
Resistance to impact	hard substrate	≥ 800 mm		(EN 12691)	
	soft substrate	≥ 1500 mm		-	
	watertight		(GB/T20624.2)		
Hail resistance	rigid substrate	≥ 17 m/s		(EN 13583)	
	flexible substrate	≥ 25 m/s		-	
Resistance to static loading	soft substrate	 ≥ 20 kg		(EN 12730)	
	rigid substrate	≥ 20 kg		-	
	watertight		(GB/T328.25)		
Tensile strength	longitudinal (md) ¹⁾	≥ 650 N/50 r	nm	(EN 12311-2)	
	transversal (cmd) ²⁾	 ≥ 650 N/50 r	nm	-	
	≥ 120 N/cm		(GB/T328.9)		
	¹⁾ md = machine direction ²⁾ cmd = cross machine direction				
Tear strength	≥ 220 N (GB/T		(GB/T328.19)		
Joint peel resistance	Failure mode: C, no failure of the joint ≥ 3 N/mm		(EN 12316-2)		
			(GB/T328.21)		
Joint shear resistance	≥ 600 N/50 mm		(EN 12317-2)		
Dimensional stability	longitudinal (md)1)	≤ 0.2 %		_ (EN 1107-2)	
	transversal (cmd)2)	≤ 0.2 %			
	≤ 0.1%		(GB/T328.13)		
	¹⁾ md = machine direction ²⁾ cmd = cross machine direction				

Sarnafil® G 410-20 L Felt 12/12/2024 File version 1.0 020905052150205003



BUILDING TRUST

Solar reflectance	0.80		(GJB 2502.2)	(GJB 2502.2)	
Solar reflectance index	106 (white, initial)		(ASTM E 1980))	
Foldability at low temperature	≤ -25 °C		(EN 495-5)		
	no crack		(GB/T328.15)		
Water absorption	wet weight	≤ 4 %		(GB 12952)	
	dry weight	≥ -0.4 %			
Watertightness	Pass		(EN 1928)		
	Watertight		(GB/T328.10)		
Water-vapour transmission rate	μ = 15 000		(EN 1931)		
Effect of liquid chemicals, in-	Tensile strength retention	≥ 85 %		(GB 12952)	
cluding water	Elongation retention	≥ 80 %			
	Low temperature bend	no crack			
Resistance to UV exposure	Pass (> 5000 h / grade 0)		(EN 1297)		
Retention of properties after	Tensile strength retention	≥ 85 %		(GB/T18244)	
heat ageing	Elongation retention	≥ 80 %			
	Low temperature bend	no crack			
Artificial ageing	Tensile strength retention	≥ 85 %		(GB/T18244)	
	Elongation retention	≥ 80 %			
	Low temperature bend	no crack			
Reaction to fire	Class E		(EN ISO 11925	-2, classification to EN 13501-1)	
	E		(GB 8624 / EN 13501-1)		
Elongation	longitudinal (md) ¹⁾		≥ 45 %		
	transversal (cmd) ²⁾		≥ 45 %		
	≥ 100 %		(GB/T328.9)		
	¹⁾ md = machine direction ²⁾ cmd = cross machine direction		achine direction		
SYSTEM INFORMATION	J				
System structure	The following products must l	be considered for	use depending or	roof design:	
	 Sarnafil[®] G 410-20 L sheet for detailing 				
	 Sarnafil[®] Metal Sheet PVC 				
	■ Sarnabar®				
	 Sarnacol[®] 2170 / 2142 / 2152 Adhesive 				
	 Sarna Cleaner 				
	Ancillary Products:				
	Prefabricated parts, roof drains, scuppers, walkway pads, decor profiles, protection sheets.				
Compatibility	Not compatible in direct conta plastic materials, e.g. expande polyisocyanurate (PIR) or pher properties, but can be isolated	act with bitumen ed polystyrene (E nolic foam (PF). T d to permit syste	, tar, fat, oil, solve PS), extruded poly These materials co m build-up.	nt containing materials and other styrene (XPS), polyurethane (PUR), uld adversely affect the product	
	Must be isolated from contact with building wrap systems (including building wraps with self-ad- hesive backings) and flashing tapes. Refer to Sika for detailing advice.				

Sarnafil® G 410-20 L Felt 12/12/2024 File version 1.0 020905052150205003

BUILDING TRUST

APPLICATION INFORMATION

Ambient air temperature	-20 °C min. / +60 °C max.
Substrate temperature	-30 °C min. / +60 °C max.

MANUFACTURER AND IMPORTER INFORMATION

Manufacturer information	Address	Sika China Ltd,	
		28 Jing Dong Road,	
		Suzhou Industrial Park, Suzhou	
		Jiangsu 215121, China	
Importer information	Address	Sika (NZ) Limited	
		85-91 Patiki Road	
		Avondale, Auckland 1026	
		New Zealand	
	Phone number	0800 745 269	
	Website	https://nzl.sika.com/	
	Email address	info@nz.sika.com	
	NZBN	9429000018791	

BUILDING CODE INFORMATION

Building Code clauses	B2 Durability: Performance clause B2.3.1 - (b) 15 years
	E2 External Moisture: Performance clauses E2.3.1, E2.3.2 and E2.3.6
	F2 Hazardous Building Materials: Performance clause F2.3.1
Building Code compliance state- ments	Performance B2.3.1 (b) 15 years: The BRANZ appraisal for this product states that, in their opinion, it achieves this durability requirement, when installed and maintained in accordance with the BRANZ Appraisal and relevant Sika technical literature. nzl.sika.com. According to Sika's "Service Improvement" records, maintained within its ISO9001:2015 Quality Management System, this product has performed successfully since it was introduced in 2014.
	Performance E2.3.1, E2.3.2 and E2.3.6: The BRANZ Appraisal for this product nzl.sika.com states that it will meet the E2.3.1, E2.3.2 and E2.3.6 weathertightness requirements when installed by a trained Sika applicator in accordance with the BRANZ Appraisal and all relevant Sika technical liter- ature nzl.sika.com
	Performance F2.3.1. The BRANZ Appraisal for this product nzl.sika.com states that, in their opinion, it meets this requirement and does not present a health hazard to people. Refer to the product safety data sheet nzl.sika.com for further information if required

BASIS OF PRODUCT DATA

All technical data in this document are based on laboratory tests. Actual measured data may vary due to circumstances beyond our control.

IMPORTANT CONSIDERATIONS

Installation work must only be carried out by Sika® trained and approved contractors, experienced in this type of application.

- Ensure Sarnafil[®] G 410-20 L Felt is prevented from direct contact with incompatible materials (refer to compatibility section).
- The use of Sarnafil[®] G 410-20 L Felt membrane is limited to geographical locations with average monthly minimum temperatures of - 50 °C. Permanent ambient temperature during use is limited to + 50°C.
- The use of some ancillary products such as adhesives, cleaners and solvents is limited to temperatures above + 5 °C. Observe temperature limitations in the appropriate Product Data Sheets.
- Special measures may be compulsory for installation below + 5°C ambient temperature due to safety requirements in accordance with national regulations.



NZ BUILDING PRODUCT INFORMATION SHEET Sarnafil® G 410-20 L Felt 12/12/2024 File version 1.0 020905052150205003

- Sarnafil[®] G 410-20 L Felt must be installed by loose laying and without stretching or installing under tension.
- Ponding water does not affect the performance properties of the membrane.

ECOLOGY, HEALTH AND SAFETY

This product is an article as defined in article 3 of regulation (EC) No 1907/2006 (REACH). It contains no substances which are intended to be released from the article under normal or reasonably foreseeable conditions of use. A safety data sheet following article 31 of the same regulation is not needed to bring the product to the market, to transport or to use it. For safe use follow the instructions given in this product data sheet. Based on our current knowledge, this product does not contain SVHC (substances of very high concern) as listed in Annex XIV of the REACH regulation or on the candidate list published by the European Chemicals Agency in concentrations above 0.1 % (w/w).

APPLICATION INSTRUCTIONS

DESIGN REQUIREMENTS

Roofs and decks must be designed and constructed to shed precipitated moisture and take account of snowfalls in snow prone areas. Refer to NZS3604 and E2/AS1 for further information.

When fully bonded, this membrane is suitable for applications in areas subject to a maximum wind pressure of 6 kPa design differential ULS, subject to the limitations of the substrate

Timber framing systems must comply with NZS3604, or where specific engineering design is used, must be of at least the equivalent stiffness requirements of NSZ 3604

Decks using Sarnafil membrane systems must be protected with either tiles or timber decking resting on Sika approved pedestal supports

All roofs and decks must be designed to have falls that are in accordance with E2/AS1 - 8.5 Membrane Roofs and Decks clause 8.5.1. Allowance for deflection and settlement of the roof substrate mut be considered, to ensure falls are maintained and water ponding on the membrane is avoided.

Separation or protection from heat sources such as fireplaces, flues, chimneys, etc must be provided to Sarnafil membrane systems. Refer to Part 7 of NZ Building Code Acceptable Solutions C/AS1 and C/AS2, and Verification Method C/VM1 for approved separation methods.

EQUIPMENT

Hot welding overlap seams Electric hot air welding equipment, such as hand held manual hot air welding equipment and pressure rollers or automatic hot air welding machines with controlled hot air temperature capability of a minimum +600 °C. Recommended type of equipment:

- Manual: Leister Triac
- Semi-automatic: Leister Triac Drive
- Automatic: Leister Varimat V2

SUBSTRATE QUALITY

The substrate surface must be uniform, smooth and free of any sharp protrusions or burrs, etc. Sarnafil® G 410-20 L Felt must be separated from any incompatible substrates / materials by an effective separation layer to prevent accelerated ageing. The supporting layer must be compatible with the membrane, solvent resistant, clean, dry and free of grease and dust. Metal sheets must be degreased with Sarna Cleaner before adhesive is applied.

APPLICATION

Installation procedure Strictly follow installation procedures as defined in method statements, application manuals and working instructions which must always be adjusted to the actual site conditions.

Fully bonded roof surfaces and detailing

The roof waterproofing membrane is bonded to the substrate using a Sarnacol[®] adhesive. The type of adhesive is selected based on the type and slope of substrate. Refer to the individual Sarnacol[®] adhesive Product Data Sheet.

Hot welding method Overlap seams must be welded by electric hot welding equipment. Welding parameters including temperature, machine speed, air flow, pressure and machine settings must be evaluated, adapted and checked on site according to the type of equipment and the climatic conditions prior to welding.

Testing overlap seams The seams must be mechanically tested with a screw driver (with rounded edges) to ensure the integrity/ completion of the weld. Any imperfections must be rectified by hot air welding.

MAINTENANCE REQUIREMENTS

For membrane cleaning requirements refer to the Sika "Roof Cleaning Guideline - Roofing and Balcony Membranes" available at nzl.sika.com.

If the membrane is damaged it must be repaired as soon as any such damage occurs. Contact Sika NZ for advice on 0800 SIKANZ

The membrane system must be checked annually (or sooner if required), for damage, rubbish, outlet blockages or coating deterioration. All debris must be removed and blockages cleared. Any damage identified must be repaired immediately. Contact Sika NZ for advice on 0800 SIKANZ

LOCAL RESTRICTIONS

Note that as a result of specific local regulations the declared data and recommended uses for this product may vary from country to country. Consult the local Product Data Sheet for the exact product data and uses.

LEGAL NOTES

The information, and, in particular, the recommendations relating to the application and end-use of Sika products, are given in good faith based on Sika's current knowledge and experience of the products when properly stored, handled and applied under normal conditions in accordance with Sika's recommendations. In practice, the differences in materials, substrates and actual site conditions are such that no warranty in respect of merchantability or of fitness for a particular purpose, nor any liability arising out of any



NZ BUILDING PRODUCT INFORMATION SHEET

Sarnafil® G 410-20 L Felt 12/12/2024 File version 1.0 020905052150205003 legal relationship whatsoever, can be inferred either from this information, or from any written recommendations, or from any other advice offered. The user of the product must test the product's suitability for the intended application and purpose. Sika reserves the right to change the properties of its products. The proprietary rights of third parties must be observed. All orders are accepted subject to our current terms of sale and delivery. Users must always refer to the most recent issue of the local Product Data Sheet for the product concerned, copies of which will be supplied on request. It may be necessary to adapt the above disclaimer to specific local laws and regulations. Any changes to this disclaimer may only be implemented with permission of Sika[®] Corporate Legal in Baar.

The building product/building product line is not subject to warning or ban under section 26 of the Building Act 2004.

Sika (NZ) Limited

85-91 Patiki Road Avondale, Auckland 1026 New Zealand 0800 745 269 www.sika.co.nz

NZ BUILDING PRODUCT INFORMATION SHEET

Sarnafil® G 410-20 L Felt 12/12/2024 File version 1.0 020905052150205003 NZBPIS-17018-7502-7502-en-GB-1.0

