Version nos: 12/11 (replaces 12/10)

SikaForce® 7010

Hardener for two component polyurethane adhesive

Technical Product Data

Chemical base	Isocyanate derivatives
Colour	Brown
Solids content	100%
Density 1) (CQP2) 006-6)	1.2 g/cm³ approx.
Viscosity 1) (CQP 538-2)	250 mPa·s approx. (Brookfield RVT 2/50)
Shelf life ³⁾	9 months

¹⁾ Testing temperature +23°C and 50% r.h. ²⁾ CQP: Corporate Quality Procedures

Description

SikaForce®-7010 is a solvent-free The following publications are dark brown liquid of low viscosity. It available on request: designed to be used in - Material Safety Data Sheet combination with SikaForce adhesive systems.

SikaForce -7010 is manufactured in accordance with ISO 9001/14001 quality assurance system and the responsible care program.

Product Benefits

- Thin liquid
- Low vapour pressure

Areas of Application

SikaForce® -7010 is a hardener for component polyurethane adhesive systems. Refer to the Product Data Sheet of the adhesive to see the fit for use. product is suitable professional experienced users only.

Cleaning

Uncured hardener on tools and application equipment can be removed with Sika Remover 208. Cured hardener can only be removed mechanically.

Storage Conditions

SikaForce®-7010 has to be kept between 10°C and 30°C in a dry place. Do not expose it to direct sunlight. After opening of the packaging, the contents should be protected against humidity

Further Information

Packaging Information

SikaForce -7010 5 kg	g kg
----------------------	---------

Important

For information and advice regarding transportation, handling, storage, and disposal of chemical products, users should refer to the actual Material Safety Data Sheet containing SikaForce® physical, ecological, toxicological and other safety related data.

Note:

The information, and, in particular, the recommendations relating to the application and end-use of Sika products, are given in good faith based on Sika's current knowledge and experience of the products when properly stored, handled and applied under normal conditions. In practice, the differences materials, substrates and actual site conditions are such that no warranty in respect of merchantability or of fitness for a particular purpose, nor any liability arising out of any legal relationship whatsoever, can be inferred either from this information, from written anv recommendations, or from any other advice offered. The proprietary rights of third parties must be observed. All orders are accepted subject to our current terms of sale and delivery. Users should always refer to the most recent issue of the Technical Data Sheet for the product concerned, copies of which will be supplied on request.







 $^{^{3)}}$ 10 -30° C